

Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Glass Fiber Reinforced Polymer Manufacturing

September 2017

(This page intentionally left blank)

Preface

Reducing energy consumption through investment in advanced technologies and practices can enhance American manufacturing competitiveness. Energy bandwidth studies of U.S. manufacturing sectors serve as general data references to help understand the range (or *bandwidth*) of potential energy savings opportunities.¹ The U.S. Department of Energy (DOE)'s Advanced Manufacturing Office (AMO) has commissioned a series of bandwidth studies to analyze the manufacturing of products that can be used for lightweighting applications, and provide hypothetical, technology-based estimates of potential energy savings opportunities in the manufacturing process. The consistent methodology used in the bandwidth studies provides a framework to evaluate and compare energy savings potentials within and across manufacturing sectors at the macro-scale.

This study is being released as part of a series of six studies focusing on energy use in the manufacture of the following lightweight structural materials: carbon fiber reinforced polymer composites, glass fiber reinforced polymer composites, advanced high-strength steel alloys, aluminum alloys, magnesium alloys, and titanium alloys. It should be noted that the boundaries of these analyses were drawn based on features of the manufacturing processes that are unique to each material. Therefore, the results of the lightweight materials bandwidth studies cannot be directly compared. In a separate study, these boundaries are redrawn to consistently include energy consumption for all phases of the product manufacturing life cycle, from the energy embodied in the raw materials through finished part fabrication (for selected applications); energy associated with end-of-life recycling is also considered. This allows the data to be integrated and compared across all six materials. This separate study also develops a framework for comparing manufacturing energy intensity on a material performance (e.g., effective weight) basis for illustrative applications.

Four different energy *bands* (or measures) are used consistently in this series to describe different levels of on-site energy consumption to manufacture specific products and to compare potential energy savings opportunities in U.S. manufacturing facilities (see figure below). **Current typical** (CT) is the energy consumption in 2010; **state of the art** (SOA) is the energy consumption that may be possible through the adoption of existing best technologies and practices available worldwide; **practical minimum** (PM) is the energy consumption that may be possible if applied research and development (R&D) technologies under development worldwide are deployed; and the **thermodynamic minimum** (TM) is the least amount of energy required under ideal conditions, which typically cannot be attained in commercial applications. CT energy consumption serves as the benchmark of manufacturing energy consumption. TM energy consumption serves as the baseline (or theoretical minimum) that is used in calculating energy savings potential. Feedstock energy (the nonfuel use of fossil energy) is not included within the energy consumption estimates.

Two on-site energy savings opportunity *bandwidths* are estimated: the **current opportunity** spans the bandwidth from CT




Figure P-1. Energy consumption bands and opportunity bandwidths estimated in this study
Source: EERE

¹ The concept of an energy bandwidth, and its use as an analysis tool for identifying potential energy saving opportunities, originated in AMO in 2002 (when it was called the Office of Industrial Technologies). Most recently, revised and consistent versions of [bandwidth studies](#) for the *Chemicals, Petroleum Refining, Iron and Steel, and Pulp and Paper* sectors were published in 2015.

energy consumption to SOA energy consumption, and the **R&D opportunity** spans the bandwidth from SOA energy consumption to PM energy consumption. The total opportunity is the sum of the R&D and the current opportunities. The difference between PM energy consumption and TM energy consumption is labeled as *impractical*. The term *impractical* is used because the PM energy consumption is based on today's knowledge of R&D technologies tested between laboratory and demonstration scale; further decreases in energy intensity have not been displayed at any physical scale. However, decreasing the PM energy consumption with future R&D efforts and emerging technologies being investigated through modeling and theoretical calculations may eventually bring the PM energy consumption closer to the TM energy consumption. Significant investment in technology development and implementation would be needed to fully realize the energy savings opportunities estimated. The costs associated with achieving SOA and PM energy consumption are not considered in this report; a techno-economic analysis of the costs and benefits of future R&D technologies was not in the scope of this study.

For each lightweighting material studied in the series, the four energy bands are estimated for select individual subareas of the material manufacturing process. The estimation method involved a detailed review and analytical synthesis of data from diverse industry, governmental, and academic sources. Where published data were unavailable, best engineering judgment was used.

Acknowledgments

Joseph Cresko of DOE/AMO led the conceptual development of the bandwidth study series, with support from Dr. Alberta Carpenter at the National Renewable Energy Laboratory. AMO recognizes the efforts of Dr. Heather Liddell, Caroline Dollinger, Dr. Aaron Fisher, and Sabine Brueske of Energetics Incorporated, who conducted the research and analysis and wrote this report. AMO wishes to acknowledge the contributions made by Jawed Asrar of Johns Manville and David Rue of the Gas Technology Institute for their work reviewing this study.

(This page intentionally left blank)

List of Acronyms and Abbreviations

ACC	American Chemistry Council
AMO	Advanced Manufacturing Office
Btu	British thermal unit
CT	Current typical energy consumption or energy intensity
DOE	U.S. Department of Energy
EERE	DOE Office of Energy Efficiency and Renewable Energy
EIA	U.S. Energy Information Administration
EPA	U.S. Environmental Protection Agency
GF	Glass fiber
GFRP	Glass fiber reinforced polymer
HDPE	High-density polyethylene
IEA	International Energy Agency
K	Kelvin
LBNL	Lawrence Berkeley National Laboratory
NREL	National Renewable Energy Laboratory
PEEK	Polyether ether ketone
PM	Practical minimum energy consumption or energy intensity
PP	Polypropylene
PS	Polystyrene
PU	Polyurethane
PVC	Polyvinyl chloride
R&D	Research and development
SOA	State of the art energy consumption or energy intensity
TBtu	Trillion British thermal units
TM	Thermodynamic minimum energy consumption or energy intensity
TP	Thermoplastic (resin)
TS	Thermoset (resin)
VSD	Variable speed drive (motor)

(This page intentionally left blank)

Executive Summary

With their high strength-to-weight ratios, glass fiber reinforced polymer (GFRP) composites have strong technical potential for lightweighting in structural applications. Also known as fiberglass, GFRP composites are used in applications such as pipes and tanks, boat hulls, wind turbine blades, and automobile bodies. However, the use of GFRP composites in many commercial applications continues to be limited by manufacturing challenges such as high costs, variable performance, poor repairability, and low process throughput. One of the most significant challenges for composite materials is their high energy intensity compared to other structural materials such as steel and aluminum.² In this report, the manufacturing energy consumption associated with the production of GFRP composites is investigated in detail. This study is limited to four energy-critical structural application areas (automotive, wind energy, aerospace, and pressure vessels), which together comprise about 47% of the total glass fiber market.

This study explores the energy intensity and energy consumption associated with GFRP manufacturing, breaking down energy use by sub-process. Energy savings opportunities are identified and quantified for each of the six manufacturing sub-processes considered:

- *Batching*: the preparation of the glass batch, including measuring, grinding and mixing the constituent materials (silica and additives)
- *Melting*: the process of melting the glass mixture and refining the molten glass to remove impurities and air bubbles
- *Fiberization*: the process of extruding the molten glass through a bushing and attenuating the extruded material into long, thin filaments
- *Finishing*: the application of surface treatments and coatings (called “sizing”) to protect the fibers and promote bonding with the plastic matrix, and the spooling of the fibers
- *Resin Production*: the manufacture of the polymer resin that will serve as a matrix material in the final composite product
- *Composite Product Forming*: the process of integrating the fibers into the polymer matrix and producing a finished composite product.

The purpose of this data analysis is to provide macro-scale estimates of energy savings opportunities for each GFRP manufacturing subarea. This is a step toward understanding the processes that could most benefit from technology and efficiency improvements to realize energy savings.

Study Organization and Approach: After providing an overview of the methodology and boundaries in Chapter 1, the 2010 production volumes for GFRP composites are estimated in Chapter 2. Current typical (CT) energy intensity and consumption are estimated for six sub-processes in Chapter 3. The state of the art (SOA) energy intensity and consumption for these processes (assuming the adoption of best technologies and practices available worldwide) is estimated in Chapter 4, and the practical minimum (PM) energy intensity and consumption for these processes (assuming the deployment of the applied research and development (R&D) technologies available worldwide) is assessed in Chapter 5. The thermodynamic minimum (TM) energy (that is, the minimum amount of energy theoretically required for these processes assuming ideal conditions) is estimated in Chapter 6; in some cases, this is less than zero. The difference between the energy consumption *bands* (CT, SOA, PM, TM) are the estimated energy savings opportunity *bandwidths*. These opportunity bandwidths are presented in Chapter 7.

Study Results: Two energy savings opportunity *bandwidths*—current opportunity and R&D opportunity—are shown in Table ES-1 and Figure ES-1.³ The current opportunity is the difference between the 2010 current typical (CT) energy consumption and the state of the art (SOA) energy consumption; the R&D opportunity is

² See the other reports in this series, *Energy Use and Potential Energy Saving Opportunities in the Manufacturing of Lightweight Materials*, for energy intensity estimates for other lightweight structural materials.

³ The energy estimates presented in this study are for macro-scale consideration; energy intensities and energy consumption values do not represent energy use in any specific facility or any particular region in the United States. The costs associated with achieving energy savings are not considered in this study. All estimates are for onsite energy use (i.e., energy consumed within the facility boundary). Energy used as feedstocks (non-fuel inputs) to production is excluded.

the difference between the SOA energy consumption and the practical minimum (PM) energy consumption. Potential energy savings opportunities are presented as a total and broken down by manufacturing sub-process. The savings total reflects a representative composite formulation, with epoxy resin assumed as the polymer matrix material and resin transfer molding assumed as the forming method. Note that the energy savings opportunities presented reflect the estimated production of GFRP composites for selected application areas in baseline year 2010. Lightweight composite materials have seen enormous growth in the past several years, especially in energy-critical applications such as automotive and wind energy. Therefore, it is important to note that the total energy opportunities would scale with increasing production.

Table ES-1. Potential Energy Savings Opportunities (On-site Energy Consumption) for GRFP Composite Manufacturing in the U.S. (Considering Production for Selected Lightweighting Application Areas Only)⁴

Opportunity Bandwidths	Estimated On-site Energy Savings Opportunity for GFRP Composite Manufacturing* (per year)
<i>Current Opportunity</i> – energy savings if the best technologies and practices available are used to upgrade production	6.63 TBtu⁵ (21.5% energy savings) ⁶
<i>R&D Opportunity</i> – additional energy savings if applied R&D technologies under development worldwide are successfully deployed	8.68 TBtu⁷ (28.1% energy savings) ⁸

⁴ Calculated using the production values for lightweight structural application areas considered in this study only (see Section 1.4), and not all glass fiber composites. Energy savings are measured from the current typical energy consumption. Note that the thermodynamic minimum (TM) is used as the baseline (rather than zero) for energy savings percent calculations.

⁵ Current opportunity = CT – SOA, as shown in Table 4-5.

⁶ Current opportunity (or SOA) percentage = $\left(\frac{CT-SOA}{CT-TM}\right) \times 100$, as shown in Table 4-5.

⁷ R&D opportunity = SOA – PM, as shown in Table 5-6.

⁸ R&D opportunity percentage = $\left(\frac{SOA-PM}{CT-TM}\right) \times 100$, as shown in Table 5-6.




Figure ES-1. Current and R&D energy savings opportunities (on-site energy consumption) for GFRP composite manufacturing by process, based on 2010 glass fiber production for structural applications
Source: EERE

The PM energy consumption estimates are speculative because they are based on unproven technologies. The estimates assume the successful deployment of R&D technologies that are under development; where multiple technologies were considered for a similar application, only the most energy efficient technology was considered in the energy savings estimate. The difference between PM and TM is labeled “impractical” in Figure ES-1 because the PM energy consumption is based on today’s knowledge of R&D technologies tested between laboratory and demonstration scale; further decreases in energy intensity have not been displayed at any physical scale. However, it is shown as a dashed line with color fading because emerging technologies being investigated through modeling and theoretical calculations may eventually bring the PM energy consumption further into the faded region and closer to the TM energy consumption.

An estimated 30.75 TBtu of energy was consumed in 2010 to manufacture GFRP composites in the United States for the four key structural applications considered in this study. Based on the results of this study, an estimated 6.63 TBtu of energy could be saved each year if state of the art technologies and manufacturing equipment available worldwide are used to upgrade GFRP manufacturing practices in the subareas studied. An additional 8.68 TBtu could be saved through the adoption of applied R&D technologies under development

worldwide. Together, these results suggest that it is potentially feasible to reduce the energy consumption associated with GFRP manufacturing by 49.8% compared to typical practices used today.

The top three current energy savings opportunities for GFRP composites are as follows:

- **Resin Production**, representing 76.2% of the current opportunity (5.05 TBtu/yr)
- **Glass Melting**, representing 15.7% of the current opportunity (1.04 TBtu/yr)
- **Composite Product Forming**, representing 4.9% of the current opportunity (0.32 TBtu/yr).

The top three R&D energy savings opportunities are as follows:

- **Resin Production**, representing 82.6% of the R&D opportunity (12.64 TBtu/yr)
- **Glass Melting**, representing 9.7% of the R&D opportunity (1.49 TBtu/yr)
- **Composite Product Forming**, representing 3.2% of the R&D opportunity (0.50 TBtu/yr).

DOE researchers will continue to evaluate the energy consumption and opportunity bandwidths in U.S. carbon fiber reinforced polymer composites manufacturing, along with bandwidth study results from other manufacturing sectors.

Table of Contents

Preface	i
Acknowledgments	iii
List of Acronyms and Abbreviations	v
Executive Summary	vii
Table of Contents.....	xi
List of Figures	xii
List of Tables	xii
1. Introduction.....	1
1.1. Overview	1
1.2. Definitions of Energy Consumption Bands and Opportunity Bandwidths	1
1.3. Bandwidth Analysis Method.....	2
1.4. Boundaries of the Study	3
2. U.S. Glass Fiber Reinforced Polymer Composite Production	5
2.1. Manufacturing Overview	5
2.2. Production Values	7
3. Current Typical Energy Intensity and Energy Consumption	11
3.1. Current Typical Energy Intensity	11
3.2. Current Typical Energy Consumption	13
4. State of the Art Energy Intensity and Energy Consumption	15
4.1. State of the Art Energy Intensity.....	15
4.2. State of the Art Energy Consumption	17
5. Practical Minimum Energy Intensity and Energy Consumption.....	20
5.1. Practical Minimum Energy Intensity	20
5.2. Practical Minimum Energy Consumption	23
6. Thermodynamic Minimum Energy Intensity and Energy Consumption	26
6.1. Thermodynamic Minimum Energy Intensity	26
6.2. Thermodynamic Minimum Energy Consumption.....	29
7. Current and R&D Opportunity Analysis/Bandwidth Summary.....	30
8. References.....	33
Appendix A1. Master GFRP Composite Summary Tables	37
Appendix A2. Fiber Ratios in Structural Lightweighting Applications.....	39
Appendix A3. Energy Mix Assumptions	40
Appendix A4. State of the Art and Practical Minimum (R&D) Technologies Considered	42
Appendix A5. Calculated Energy Intensity of Oxygen Production	48

List of Figures

Figure P-1. Energy consumption bands and opportunity bandwidths estimated in this study.....	i
Figure ES-1. Current and R&D energy savings opportunities (on-site energy consumption) for GFRP composite manufacturing by process, based on 2010 glass fiber production for structural applications	ix
Figure 1-1. Energy consumption bands and opportunity bandwidths estimated in this study	1
Figure 1-2. Estimated makeup of the glass fiber market in 2010 (glass rovings only).....	4
Figure 2-1. Process flow diagram for glass fiber reinforced polymer composite manufacturing.....	6
Figure 7-1. Current and R&D energy savings opportunities (on-site energy consumption) for GFRP composite manufacturing by process, based on 2010 glass fiber production for structural applications.....	32

List of Tables

Table ES-1. Potential Energy Savings Opportunities (On-site Energy Consumption) for GRFP Composite Manufacturing in the U.S. (Considering Production for Selected Lightweighting Application Areas Only) ...	viii
Table 2-1. Glass Fiber Reinforced Composites Manufacturing Process Subareas and Sub-Processes Considered in the Bandwidth Analysis	7
Table 2-2. Global and U.S. Production of Glass Fiber Reinforced Polymer Composites in 2010 (Glass Rovings Only)	8
Table 3-1. Current Typical Energy Intensity for Production of Glass Fibers	11
Table 3-2. Current Typical Energy Intensity for Production of Matrix Resins	12
Table 3-3. Current Typical Energy Intensity for Composite Product Forming	13
Table 3-4. Calculated Current Typical Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied (2010).....	14
Table 4-1. State of the Art Energy Intensity for Production of Glass Fibers	15
Table 4-2. State of the Art Energy Intensity for Production of Matrix Resins	16
Table 4-3. State of the Art Energy Intensity for Composite Product Forming	17
Table 4-4. Calculated State of the Art Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied	18
Table 4-5. Calculated State of the Art Energy Savings for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied	19
Table 5-1. Practical Minimum Energy Intensity for Production of Glass Fibers.....	21
Table 5-2. Practical Minimum Energy Intensity for Production of Matrix Resins.....	22
Table 5-3. Practical Minimum Energy Intensity for Composite Product Forming.....	22
Table 5-4. Calculated Practical Minimum Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied	23
Table 5-5. Calculated Practical Minimum Energy Savings for Glass Fiber Composite Manufacturing: Application Areas Studied	24
Table 5-6. Calculated Practical Minimum Energy Consumption, R&D Opportunity, and R&D Opportunity Percent for Glass Fiber Composite Manufacturing: Application Areas Studied	25
Table 6-1. Thermodynamic Minimum Energy Intensity for Production of Glass Fibers	27
Table 6-2. Thermodynamic Minimum Energy Intensity for Production of Matrix Resins	28
Table 6-3. Thermodynamic Minimum Energy Intensity for Composite Product Forming	28
Table 6-4. Calculated Thermodynamic Minimum Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied	29
Table 7-1. Current and R&D Opportunities for GFRP Manufacturing (On-site Energy Consumption): Application Areas Studied	30
Table 7-2. Manufacturing Process Assumptions for Current Typical, State of the Art, and Practical Minimum Energy Bands.....	30
Table A1-1. On-site Energy Intensity and Energy Consumption Estimates for GFRP Composite Manufacturing for the Four Bandwidth Measures, Based on 2010 Production of GFRP Composites for Structural Application Areas	37

Table A1-2. Primary Energy Intensity and Energy Consumption Estimates for GFRP Composite Manufacturing for the Four Bandwidth Measures, Based on 2010 Production of GFRP Composites for Structural Application Areas.....	38
Table A2-1. Fiber/Matrix Polymer Ratios: Automotive Case Studies.....	39
Table A3-1. Energy Mix Assumptions for GFRP Composite Manufacturing Processes	41
Table A4-1. Details of Practical Minimum Technologies Considered	42
Table A3-1. Calculated On-site Energy Intensity of VSA, PSA, and Cryogenic Oxygen Production	48

(This page intentionally left blank)

1. Introduction

1.1. Overview

The U.S. Department of Energy (DOE)'s Advanced Manufacturing Office (AMO) has commissioned a series of bandwidth studies to analyze processes and products that are highly energy intensive, and provide hypothetical, technology-based estimates of energy savings opportunities. Reducing energy consumption through investment in advanced technologies and practices can enhance American manufacturing competitiveness. Manufacturing energy bandwidth studies serve as general data references to help understand the range (or *bandwidth*) of energy savings opportunities. DOE AMO commissioned this bandwidth study to analyze the most energy consuming processes in manufacturing glass fiber-reinforced polymer (GFRP) composites.

This bandwidth study is one in a series of six bandwidth studies characterizing energy use in manufacturing lightweight structural materials in the United States. The other materials, studied in parallel, include: aluminum alloys, magnesium alloys, titanium alloys, advanced high strength steel alloys, and carbon fiber reinforced composites. Separate studies are available for these materials. As a follow-up to this work, an integrating analysis will be conducted to compare results across all six studies.

Similar energy bandwidth studies have also been prepared for four U.S. manufacturing sectors: petroleum refining (Energetics (2015a)), chemicals (Energetics (2015b)), iron and steel (Energetics (2015c)), and pulp and paper (Energetics (2015d)). These studies followed the same analysis methodology and presentation format as the six lightweight structural material energy bandwidth studies.

1.2. Definitions of Energy Consumption Bands and Opportunity Bandwidths

The consistent methodology used in the bandwidth studies provides a framework to evaluate and compare energy savings potentials within and across manufacturing sectors at the macro-scale.

Four different energy *bands* (or measures) are used consistently in this series to describe different levels of on-site energy consumption to manufacture specific products and to compare energy savings opportunities in U.S. manufacturing facilities. **Current typical** (CT) is the energy consumption in 2010; **state of the art** (SOA) is the energy consumption that may be possible through the adoption of existing best technologies and practices available worldwide; **practical minimum** (PM) is the energy consumption that may be possible if applied R&D technologies under development worldwide are deployed; and the **thermodynamic minimum** (TM) is the least amount of energy required under ideal conditions, which typically cannot be attained in commercial applications.

CT energy consumption serves as the benchmark of manufacturing energy consumption. TM energy consumption serves as the baseline (or theoretical minimum) that is used in calculating energy savings potential. Feedstock energy (the nonfuel use of fossil energy) is not included in the energy consumption estimates.




Figure 1-1. Energy consumption bands and opportunity bandwidths estimated in this study
Source: EERE

Two on-site energy savings opportunity *bandwidths* are estimated: the **current opportunity** spans the bandwidth from CT energy consumption to SOA energy consumption, and the **R&D opportunity** spans the bandwidth from SOA energy consumption to PM energy consumption. These bandwidths are estimated for processes and products studied and for all manufacturing within a sector based on extrapolated data. The difference between PM energy consumption and TM energy consumption is labeled as *impractical*. The term *impractical* is used because the PM energy consumption is based on today's knowledge of R&D technologies tested between laboratory and demonstration scale; further decreases in energy intensity have not been displayed at any physical scale. However, decreasing the PM energy consumption with future R&D efforts and emerging technologies being investigated through modeling and theoretical calculations may eventually bring the PM energy consumption closer to the TM energy consumption. Significant investment in technology development and implementation would be needed to fully realize the energy savings opportunities estimated. The costs associated with achieving SOA and PM energy consumption are not considered in this report; a techno-economic analysis of the costs and benefits of future technologies was not within the scope of this study.

1.3. Bandwidth Analysis Method

This section describes the method used in this bandwidth study to estimate the four bands of energy consumption and the two corresponding energy savings opportunity bandwidths. This section can also be used as a guide to understanding the structure and content of this report.

In this study, U.S. energy consumption is labeled as either “on-site energy” or “primary energy” and defined as follows:

- **On-site energy** (sometimes referred to as site or end use energy) is the energy consumed within the manufacturing plant boundary (i.e., within the plant gates). Non-fuel feedstock energy is not included in the on-site energy consumption values presented in this study.
- **Primary energy** (sometimes referred to as source energy) includes energy that is consumed both off-site and on-site during the manufacturing process. Off-site energy consumption includes generation and transmission losses associated with bringing electricity and steam to the plant boundary. Non-fuel feedstock energy is not included in the primary energy values. In some cases, references do not differentiate steam from fuel as an energy source, and without a better estimate it is difficult to determine what portion of steam losses should be accounted for in primary energy. Primary energy is frequently referenced by governmental organizations when comparing energy consumption across sectors.

The four bands of energy consumption described above were quantified for process subareas and for the material total. **The bands of energy consumption and the opportunity bandwidths presented herein consider on-site energy consumption; feedstocks⁹ are excluded.** To determine the total annual CT, SOA, PM, and TM energy consumption (TBtu per year), energy intensity values per unit weight (Btu per pound of material manufactured) were estimated and multiplied by the annual production total (pounds of material manufactured per year). The year 2010 was used as a base year since it is the most recent year for which consistent energy consumption and production data were available for all six lightweight materials analyzed in this series of bandwidth studies. Unless otherwise noted, 2010 production data were used.

Chapter 2 presents the **U.S. production** (million pounds per year) for 2010, including an overview of major application areas. Four structural application areas for GFRP composites are included within the scope of this bandwidth report. The production volumes for these application areas are estimated from market data.

Chapter 3 presents the estimated on-site **CT energy intensity** (Btu per pound) and **CT energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources and assumptions).

Chapter 4 presents the estimated on-site **SOA energy intensity** (Btu per pound) and **SOA energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources and assumptions).

⁹ Feedstock energy is the nonfuel use of combustible energy.

Chapter 5 presents the estimated on-site **PM energy intensity** (Btu per pound) and **PM energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources and assumptions).

Chapter 6 presents the estimated on-site **TM energy intensity** (Btu per pound) and **TM energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources and assumptions).

Chapter 7 provides a summary of **current and R&D opportunity** analysis based on bandwidth study results.

1.4. Boundaries of the Study

The U.S. GFRP composites manufacturing sector is the physical boundary of this study. It is recognized that the major benefits of using GFRP composites as lightweight materials often occur *outside* of the manufacturing sector—for example, the energy benefits of a lightweight automobile component are typically realized primarily through fuel savings during the vehicle’s use phase. Economic impacts are also important: an advanced lightweight aerospace component may be more expensive than the conventional choice. While such impacts are recognized as important, they will not be quantified as this is not a life cycle assessment study. Instead, this report focuses exclusively on the energy use directly involved in the production of glass fiber composites from the relevant input materials. The focus of this bandwidth study is thus the *on-site* use of process energy (including purchased energy and on-site generated steam and electricity) that is directly applied to GFRP manufacturing at a production facility.

This study does not consider life cycle energy consumed during raw material extraction, off-site treatment, transportation of materials, product use, or disposal. For consistency with previous bandwidth studies, feedstock energy and the energy associated with delivering feedstocks to the plant gate (e.g., producing, conditioning, and transporting feedstocks) are *excluded* from the energy consumption bands in this analysis.

Glass fibers and fiber-reinforced composites are used in many diverse applications that differ substantially in product use, performance requirements, and relevance to energy use. GFRP materials have strong lightweighting potential in transportation applications, where mass reductions in structural and semi-structural parts can provide substantial energy savings through improved fuel economy. These applications are of high relevance to the DOE because of the potential life cycle energy savings. Other applications, however, are less relevant to the DOE; for example, glass fibers are used in products such as reinforced cement, insulation, sporting equipment, and electrical devices. In order to focus exclusively on structural applications with strong relevance to energy use, this study was limited to four key application areas:

- 1) Automotive lightweighting (e.g., vehicle chassis, body, doors)
- 2) Compressed gas storage (e.g., hydrogen fuel tanks for electric vehicles)
- 3) Wind turbines (e.g., lighter and longer turbine blades)
- 4) Aerospace (e.g., aircraft fairings, fuselages, floor panels).

The first three of these application areas are consistent with the areas of interest outlined in the DOE *Composite Materials and Structures* Funding Opportunity Announcement (DOE (2014)). The last application area (aerospace) is an additional high value-add market for lightweight structural materials. Together, the four application areas considered in this study account for approximately 47% of overall glass fiber (rovings) production in the United States, as shown in Figure 1-2.¹⁰ Amongst these four application areas, automotive represents the largest market, accounting for 31% of glass rovings production overall and 66% of production for the four structural application areas considered in this report.

¹⁰ Data sources: JEC (2011) for production data; JEC (2012) for application breakdown data. Note that Figure 1-1 shows production data for glass rovings only (and excludes glass yarns). Glass yarns are generally woven into fabrics and are not used in structural composites. For further discussion, see Section 2.2.




Figure 1-2. Estimated makeup of the glass fiber market in 2010 (glass rovings only).
Source: EERE

Production of GFRP composites for applications that are outside of the boundaries of this study will be discussed briefly in Chapter 2, but energy consumption will not be quantified. These other applications may include medical devices, electronics and communications, computers and electrical equipment, construction and infrastructure materials, and consumer goods and packaging.

2. U.S. Glass Fiber Reinforced Polymer Composite Production

2.1. Manufacturing Overview

Figure 2-1 shows the GFRP composite manufacturing process schematically. The manufacturing process can be divided into six main process steps:

- *Batching*: the preparation of the glass batch, including measuring, grinding and mixing the constituent materials (silica and additives)
- *Melting*: the process of melting the glass mixture and refining the molten glass to remove impurities and air bubbles
- *Fiberization*: the process of extruding the molten glass through a bushing and attenuating the extruded material into long, thin filaments
- *Finishing*: the application of surface treatments and coatings (called “sizing”) to protect the fibers and promote bonding with the plastic matrix, and the spooling of the fibers
- *Resin Production*: the manufacture of the polymer resin that will serve as a matrix material in the final composite product
- *Composite Product Forming*: the process of integrating the fibers into the polymer matrix and producing a finished composite product.

These process steps are further identified in Table 2-1, noting that the first four process steps listed (batching, melting, fiberization, and finishing) are sub-processes of glass fiber production. Six different polymer matrix materials were considered in this study, including two thermosetting polymers (epoxy¹¹ and polyurethane¹²) and four thermoplastic polymers (polypropylene, high-density polyethylene, polyvinyl chloride,¹³ and polystyrene¹⁴). Ten composite product forming techniques were considered, including two intermediate (semi-finished) manufacturing techniques (pre-impregnated fabric or “prepreg,” and sheet or bulk molding compounds), and eight direct forming methods (hand lay-up or spray up, filament winding, pultrusion, injection molding, compression molding, resin transfer molding [including vacuum-assisted resin infusion], thermoforming, and cold press). Direct molding processes result in a finished component, whereas intermediate manufacturing techniques result in a semi-finished product (typical a fabric, molding compound, or tape) that must undergo additional process steps to form the finished component. The energy consumed in these further process steps, which are often carried out off site by an end-use manufacturer, was not considered in this analysis.

Additional resin materials and product forming techniques that are commonly used in composites manufacturing, but that were not included in this bandwidth analysis, are listed in Table 2-1 for reference.

Energy intensity and consumption are evaluated by process area and sub-process for CT, SOA, PM, and TM in Chapters 3 through 6 of this report. Appendix A1 provides a summary of all data. To determine the total energy consumption for a given composite product, it is necessary to first sum the energy consumption for all four sequential glass fiber production steps, then add the energy consumption for the selected resin material and product forming technique in a “mix-and-match” fashion. In this report, epoxy is used as the resin material and resin transfer molding is used as the product forming technique anywhere a total energy intensity or consumption is presented. However, readers may substitute values for other resins or processes into the formulae provided in this report to determine totals for other combinations.

¹¹ The epoxy system considered was bisphenol-A and epichlorohydrin. Epoxy hardeners were not considered.

¹² The polyurethane material considered was rigid polyurethane foam.

¹³ The polyvinyl chloride material considered was produced via bulk polymerization.

¹⁴ The polystyrene material considered was general-purpose polystyrene (GPPS) produced via continuous-mass radical polymerization.

Glass Fiber Process Flow Diagram




Figure 2-1. Process flow diagram for glass fiber reinforced polymer composite manufacturing
Source: EERE

Table 2-1. Glass Fiber Reinforced Composites Manufacturing Process Subareas and Sub-Processes Considered in the Bandwidth Analysis

Subareas	Sub-processes/products
Glass Fiber Production (four sequential steps)	<ul style="list-style-type: none"> - Batching - Melting - Fiberization - Finishing
Resin Production	<p><u>Thermosetting Resins:</u></p> <ul style="list-style-type: none"> - Epoxy - Polyurethane - Vinyl ester* - Polyester* - Phenolic* - Polyimide* <p><u>Thermoplastic Resins:</u></p> <ul style="list-style-type: none"> - Polypropylene (PP) - High-density polyethylene (HDPE) - Polyvinyl chloride (PVC) - Polystyrene (PS) - Polyether ether ketone (PEEK)* - Polyamide (e.g., Nylon)*
Composite Product Forming	<p><u>Intermediate (Semi-finished) Manufacturing Methods:</u></p> <ul style="list-style-type: none"> - Prepreg (fabrics and tapes) - Sheet or bulk molding compound - Compounded thermoplastic pellets* <p><u>Direct Forming Methods:</u></p> <ul style="list-style-type: none"> - Open molding (hand lay-up or spray up) - Filament winding - Pultrusion - Injection molding - Compression molding - Resin transfer molding (including vacuum infusion) - Thermoforming - Cold press - Overmolding*

* Included in list for reference but not analyzed in this report.

2.2. Production Values

Production data for 2010 are summarized in Table 2-2, which shows the global production, U.S. production, and estimated U.S. production for the boundary applications. In 2010, United States manufacturers produced an estimated total of 1,925 million pounds of glass fibers,¹⁵ representing about 18% of global production (JEC (2011)). About 81% of the fibers produced were *glass rovings* (large-diameter [$\geq 10 \mu\text{m}$] filaments that can be used as a reinforcement in structural composites), while the remaining 19% were *glass yarns* (flexible, small-diameter [$< 10 \mu\text{m}$] filaments that are generally woven into fabrics). Glass yarns were excluded in this study as

¹⁵ Assumes that 90% of North American production occurs in the U.S. Note that his production total includes fiber production only (not the production of GFRP composites, which would utilize the glass fibers as an input).

they are not used in structural composites. For glass rovings only, estimated production totals were 1,568 million pounds for U.S. manufacturers and 8,466 million pounds globally in 2010. Total fiber production was broken down by application area using data from a market report (JEC (2012)) to estimate the quantity of glass fibers produced for the four boundary applications (automotive, wind energy, compressed gas storage, and aerospace). An estimated 737 million pounds of glass fibers were used in these boundary applications, as shown in Figure 1-1.

Table 2-2. Global and U.S. Production of Glass Fiber Reinforced Polymer Composites in 2010 (Glass Rovings Only)

Subarea	Product	2010 Total Global Production (million lbs/yr)	2010 Total U.S. Production (million lbs/yr)	2010 Estimated U.S. Production for Boundary Applications (million lbs/ yr)
Glass Fiber Production (Glass Rovings)	Glass fiber	8,466	1,568	737
Resin Production for Structural GFRP Composites	Matrix resin	n/a*	n/a*	737
Structural Composite Production**	Composite product	n/a*	n/a*	1,473

* Not calculated because some fibers outside of the boundary applications were not used in the production of fiber-reinforced polymer composites.

** Structural composite production represents the sum of glass fiber reinforcement production (for boundary applications) and resin production (for boundary applications, assuming a 50:50 weight ratio of fibers to polymer); independent rounding explains why the values do not sum in this summary table.

Resin and composite production values were calculated by assuming a 50:50 weight ratio of fiber reinforcement to polymer matrix.¹⁶ The resin production numbers, therefore, are an estimate of the production of resins for use in glass fiber composites only, and do not reflect the total production of these materials in the U.S. for all applications. Global and U.S. production values for resins and composites were calculated only for the boundary applications, as some glass fibers outside of the boundary applications were not used in the production of fiber-reinforced polymer composites. For example, glass fibers are used in the construction industry for cement reinforcement and insulation; such fibers would not be integrated into a polymer matrix and thus are not included in the production totals.

¹⁶ It is noted that fiber ratio in a GFRP composite can vary widely depending on the specific performance requirements in the application, but a 50:50 weight ratio is considered representative of structural lightweighting applications. This weight ratio was the median value in seven lightweighting case studies for automotive applications identified in a literature review (see Appendix A2 for details).

3. Current Typical Energy Intensity and Energy Consumption

This chapter presents energy intensity and consumption data for GFRP manufacturing processes, based on 2010 production data for the boundary application areas. It is noted that energy consumption in a manufacturing process can vary widely for diverse reasons, including production volume, differences in equipment, and the specific processing techniques employed at any given facility. The energy intensity estimates reported herein are considered representative of typical processes used to produce GFRP composites in the U.S. today; they do not represent energy consumption in any specific facility or any particular region in the United States.

3.1. Current Typical Energy Intensity

Table 3-1 presents the estimated CT energy intensities for glass fibers. Energy intensities for all sub-processes are presented in terms of Btu per pound (Btu/lb) of finished glass fibers. Data were drawn from a 2007 report from the Gas Technology Institute, *Industrial Glass Bandwidth Analysis* (Rue (2007)), which quantified the average energy intensity of major glassmaking process steps for five different glass industry segments, including glass fibers. On-site CT energy intensity data were converted to primary energy data using process-specific energy mix assumptions, taking into account the relative use of electricity and fuel in each sub-process. Primary energy includes off-site energy generation and transmission losses. These assumptions are described in Appendix A3. CT energy intensity estimates for melting were adjusted to account for the energy intensity of oxygen generation for use in oxygen-gas-fired glass furnaces. These assumptions and calculations used to make these adjustments are described in Appendix A5.

Table 3-1. Current Typical Energy Intensity for Production of Glass Fibers

Glass Fiber Production Sub-Process	On-site CT Energy Intensity (Btu/lb)	Primary* CT Energy Intensity (Btu/lb)	Data Source
Batching	340	1,054	Rue (2007)
Melting	3,450	3,931	Rue (2007)
Fiberization	751	1,160	Rue (2007)
Finishing	751	829	Rue (2007)
Total Energy Intensity for Glass Fibers**	5,292	6,974	

Current Typical (CT)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

** Totals may not sum due to independent rounding.

Table 3-2 presents the estimated CT energy intensities for the six matrix resin materials studied. Energy intensities are presented in terms of Btu per pound (Btu/lb) of resin. For polypropylene (PP), high-density polyethylene (HDPE), polyvinyl chloride (PVC), and polystyrene (PS), data were drawn from the 2011 American Chemistry Council report, *Cradle-to-Gate Life Cycle Inventory of Nine Plastic Resins and Four Polyurethane Precursors*. This report quantified average energy use for resin manufacturing based on primary energy data submitted by 80 different resin/precursor manufacturing plants in North America. These data are considered very high quality, and representative of U.S. production. For epoxy resin and polyurethane resin, ACC data were not available. For these materials, data were drawn from the PlasticsEurope *Eco-Profiles*. The energy data reported in the *Eco-Profiles* are representative of average production processes in Europe, and are similarly high quality. Where data were available from both sources, ACC and PlasticsEurope energy intensity

data were in excellent agreement ($\leq 10\%$ difference between values), indicating that energy use in U.S. and European plants are generally similar for the resins considered. Note that feedstock energy is not included in the energy intensities reported here for consistency with past bandwidth reports.¹⁷

Table 3-2. Current Typical Energy Intensity for Production of Matrix Resins

Matrix Polymer	On-site CT Energy Intensity (Btu/lb)	Primary* CT Energy Intensity (Btu/lb)	Data Source
Thermosetting Resins			
Epoxy resin	34,256	40,105	PlasticsEurope (2006)
Polyurethane resin	11,398	27,355	PlasticsEurope (2005b)
Thermoplastic Resins			
Polypropylene (PP)	5,227	11,822	ACC (2011)
High density polyethylene (HDPE)	6,845	14,617	ACC (2011)
Polyvinyl chloride (PVC)	9,158	15,261	ACC (2011)
Polystyrene (PS)	10,751	18,099	ACC (2011)

Current Typical (CT)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

Current typical energy intensity values for composite product forming are presented in Table 3-3, along with the sources used. Energy intensities are presented in terms of Btu per pound (Btu/lb) of composite product (fibers and resin).

¹⁷ Feedstock energies were given in both ACC and PlasticsEurope data, but were subtracted from the totals in this analysis.

Table 3-3. Current Typical Energy Intensity for Composite Product Forming

Forming Method	On-site CT Energy Intensity (Btu/lb)	Primary* CT Energy Intensity (Btu/lb)	Data Source
Intermediate (Semi-finished) Manufacturing Methods			
Prepreg	17,196	53,238	Suzuki & Takahashi (2005)
Sheet or bulk molding compound	1,505	4,658	Suzuki & Takahashi (2005)
Direct Forming Methods			
Open molding (hand lay-up or spray up)	2,237	5,805	USLCI (2012)
Filament winding	1,161	3,594	Suzuki & Takahashi (2005)
Pultrusion	1,333	4,126	Suzuki & Takahashi (2005)
Injection molding	2,794	8,651	MFI (2016)
Compression molding	2,632	7,790	USLCI (2012)
Resin transfer molding (including vacuum infusion)	1,093	2,014	USLCI (2012)
Thermoforming	11,048	33,935	Franklin (2011)
Cold press	5,073	15,705	Suzuki & Takahashi (2005)

Current Typical (CT)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

3.2. Current Typical Energy Consumption

Table 3-4 presents the calculated on-site and primary CT energy consumption for the GFRP production subareas studied. In these summary data, epoxy resin was assumed as the polymer matrix material and resin transfer molding was assumed as the composite product forming method. These selections are considered representative of current typical fiber-reinforced polymer composite systems for structural applications. Energy consumption values were calculated by multiplying energy intensity (Btu/lb) by 2010 production (lbs). As described in the previous section, on-site energy intensities were converted to primary (and vice versa) using process-specific energy mix data, as described in Appendix 3. Some data sources provided primary values and others provided on-site values; off-site losses attributed to electricity generation and transmission are accounted for in the conversion between the on-site and primary.

Table 3-4. Calculated Current Typical Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied (2010)

Subarea (product)	On-site CT Energy Intensity (Btu/lb)	Primary CT Energy Intensity (Btu/lb)	Production (million lbs)	On-site CT Energy Consumption (TBtu/yr)	Off-site Losses, Calculated (TBtu/yr)	Primary CT Energy Consumption (TBtu/yr)
Glass Fiber Production (glass fibers)						
Batching	340	1,054	737	0.25	0.53	0.78
Melting	3,450	3,931	737	2.54	0.36	2.90
Fiberization	751	1,160	737	0.55	0.30	0.85
Finishing	751	829	737	0.55	0.06	0.61
Resin Production* (matrix polymer)	34,256	40,105	737	25.24	4.31	29.55
Composite Product Forming** (composite product)	1,093	2,014	1,473	1.61	1.36	2.97
Total***				30.75	6.91	37.65

Current Typical (CT)

* Assumes thermosetting epoxy resin.

** Assumes resin transfer molding.

***Note: totals may not sum due to independent rounding.

4. State of the Art Energy Intensity and Energy Consumption

This chapter estimates the energy savings possible if U.S. glass fiber, resin, and composites manufacturers were to adopt the best technologies and practices available worldwide. State of the art (SOA) energy intensity is considered the minimum amount of energy needed for a specific process, assuming use of best-available commercial technologies and practices. The SOA energy intensity estimates reflect the use of a combination of state-of-the-art technologies, and do not represent energy consumption or manufacturing practices in any specific facility or any particular region in the United States or globally.

4.1. State of the Art Energy Intensity

Table 4-1 presents the estimated SOA energy intensities for glass fibers. Energy intensities for all sub-processes are presented in terms of Btu per pound (Btu/lb) of finished glass fibers. The SOA energy intensity for melting, obtained from Rue (2007), was adjusted to account for the energy intensity of oxygen generation, assuming cryogenic oxygen generation. The calculations and assumptions used to estimate the energy intensity of cryogenic oxygen generation are included in Appendix A5. SOA energy intensity estimates for batching, fiberization, and finishing were not found in published reports during the literature search. Instead, SOA estimates were calculated by applying assumed energy savings percentages for applicable SOA technologies to the baseline CT energy intensities for each manufacturing sub-process. The SOA technologies included in this analysis and assumed energy savings were:

- **Moderate glass fiber recycling:** 9% savings in all subprocesses
- **Advanced process control systems:** 3% energy savings in batching and finishing; 6.5% energy savings in fiberization
- **Motor re-sizing or VSDs:** 12% savings in batching and forming processes.

For a discussion of these technologies and energy savings estimates, including references, see Appendix A4, which also provides details of additional technologies that were considered but not included in the final SOA calculations. As noted earlier, the SOA value for glass melting was drawn directly from the literature. However, Appendix A4 lists technologies applicable to glass melting as well. On-site data were converted to primary data using process-specific energy mix assumptions, taking into account the relative use of electricity and fuel in each sub-process. These assumptions are described in Appendix A3.

Table 4-1. State of the Art Energy Intensity for Production of Glass Fibers

Glass Fiber Production Sub-Process	On-site SOA Energy Intensity (Btu/lb)	Primary* SOA Energy Intensity (Btu/lb)	Data Source
Batching	264	818	Calculated
Melting	2,039	2,368	Rue (2007)
Fiberization	619	957	Calculated
Finishing	663	732	Calculated
Total Energy Intensity for Glass Fibers**	3,586	4,875	

State of the Art (SOA)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

** Totals may not sum due to independent rounding.

For resin production, SOA energy intensity values were estimated by assuming a 20% energy savings over the lower of the current average primary energy intensity values reported for U.S. plants (based on ACC data) and European plants (based on PlasticsEurope data). The 20% savings figure is consistent with the ACC report (ACC (2011)), which stated that “individual plant results varied as much as 25 percent on either side of the average total energy.” Table 4-2 presents the estimated SOA energy intensities for the six matrix polymer materials studied. Note that feedstock energy is not included in the energy intensities reported here for consistency with past bandwidth reports.¹⁸

SOA energy intensity values for composite product forming are presented in Table 4-3. For injection molding, a best practice energy intensity was available from a literature source. For the other processes, no best practice/best plant values were available in the literature; for these processes, the SOA intensity was assumed to be 20% lower than the current typical intensity. This assumption is in line with the findings of ACC (ACC (2011)) and represents the authors’ best engineering judgment.

Table 4-2. State of the Art Energy Intensity for Production of Matrix Resins

Matrix Polymer	On-site SOA Energy Intensity (Btu/lb)	Primary* SOA Energy Intensity (Btu/lb)	Data Source
Thermosetting Resins			
Epoxy resin	27,405	32,084	Best engineering judgment (PlasticsEurope (2006) + 20% savings)
Polyurethane resin	9,118	21,884	Best engineering judgment (PlasticsEurope (2005a) + 20% savings)
Thermoplastic Resins			
Polypropylene (PP)	4,182	9,458	Best engineering judgment (ACC (2011) + 20% savings)
High density polyethylene (HDPE)	4,461	9,527	Best engineering judgment (ACC (2011) + 20% savings)
Polyvinyl chloride (PVC)	6,666	11,109	Best engineering judgment (PlasticsEurope (2005b) + 20% savings)
Polystyrene (PS)	8,249	13,887	Best engineering judgment (PlasticsEurope (2012) + 20% savings)

State of the Art (SOA)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

¹⁸ Feedstock energies were given in both ACC and PlasticsEurope data, but were subtracted from the totals in this analysis.

Table 4-3. State of the Art Energy Intensity for Composite Product Forming

Production Method	On-site SOA Energy Intensity (Btu/lb)	Primary* SOA Energy Intensity (Btu/lb)	Data Source
Intermediate (Semi-finished) Manufacturing Methods			
Prepreg	11,757	42,591	Best engineering judgment (20% savings)
Sheet or bulk molding compound	1,204	3,727	Best engineering judgment (20% savings)
Direct Forming Methods			
Open molding (hand lay-up or spray up)	1,696	3,506	USLCI (2012)
Filament winding	929	2,875	Best engineering judgment (20% savings)
Pultrusion	1,066	3,301	Best engineering judgment (20% savings)
Injection molding	925	2,863	Thiriez (2006)
Compression molding	2,106	6,232	Best engineering judgment (20% savings)
Resin transfer molding (including vacuum infusion)	874	1,611	Best engineering judgment (20% savings)
Thermoforming	8,839	27,148	Best engineering judgment (20% savings)
Cold press	4,058	12,564	Best engineering judgment (20% savings)

State of the Art (SOA)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%.

Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

4.2. State of the Art Energy Consumption

Table 4-4 presents the calculated on-site and primary SOA energy consumption for the GFRP production subareas studied. In these summary data, epoxy resin was assumed as the polymer matrix material and resin transfer molding was assumed as the composite product forming method. These selections are considered representative of current state of the art composite systems for structural applications. Energy consumption values were calculated by multiplying energy intensity (Btu/lb) by 2010 production (lbs). On-site energy intensities were converted to primary (and vice versa) using process-specific energy mix data, as described in Appendix 3. Some data sources provided primary values and others provided on-site values; off-site losses attributed to electricity generation and transmission are accounted for in the conversion between the on-site and primary.

Table 4-4. Calculated State of the Art Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied

Subarea (product)	On-site SOA Energy Intensity (Btu/lb)	Primary SOA Energy Intensity (Btu/lb)	Production (million lbs)	On-site SOA Energy Consumption (TBtu/yr)	Off-site Losses, Calculated (TBtu/yr)	Primary SOA Energy Consumption (TBtu/yr)
Glass Fiber Production (glass fibers)						
Batching	264	818	737	0.19	0.41	0.60
Melting	2,039	2,368	737	1.50	0.24	1.74
Fiberization	619	957	737	0.46	0.25	0.71
Finishing	663	732	737	0.49	0.05	0.54
Resin Production* (matrix polymer)	27,405	32,084	737	20.19	3.45	23.64
Composite Product Forming** (composite product)	874	1,611	1,473	1.29	1.09	2.37
Total***				24.12	5.48	29.60

State of the Art (SOA)

* Assumes thermosetting epoxy resin.

** Assumes resin transfer molding

***Note: totals may not sum due to independent rounding.

Table 4-5 presents a comparison of the on-site CT energy consumption and SOA energy consumption for each process subarea and as a total. The difference between the CT and SOA energy consumption values is presented as the SOA energy savings (or *current opportunity*). The SOA energy savings percent in Table 4-5 is the percent of energy saved with SOA energy consumption compared to CT energy consumption, while referencing the thermodynamic minimum as the baseline energy consumption. Thermodynamic minimum (TM), discussed further in Chapter 6, is considered to be equal to zero in an ideal case with perfect efficiency (i.e., energy input to a system is considered fully recoverable with no friction losses or change in surface energy). For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical reaction or permanent crystalline change due to deformation), TM is not necessarily equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0). Referencing TM as the baseline in comparing bandwidths of energy consumption and calculating energy savings percent provides the most accurate measure of absolute savings potential. The equation for calculating on-site SOA energy savings percent is:

$$SOA\ Savings\ \% = current\ opportunity\ \% = \frac{CT - SOA}{CT - TM}$$

It is useful to consider both TBtu energy savings and energy savings percent when comparing energy savings opportunities. Both are good measures of opportunity; however, the conclusions are not always the same. A small percent energy reduction in a process that consumes a large amount of energy may result in a larger total savings than a large percent reduction in a process that consumes a relatively smaller amount of energy. Among the processes studied, the greatest *current opportunity* in terms of percent energy savings is glass melting at 47.3% energy savings; the greatest *current opportunity* in terms of TBtu savings is resin production at 5.05 TBtu per year savings.

Table 4-5. Calculated State of the Art Energy Savings for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied

Subarea (product)	On-site CT Energy Consumption, Calculated (TBtu/yr)	On-site SOA Energy Consumption, Calculated (TBtu/yr)	SOA Energy Savings* (CT - SOA) (TBtu/yr)	SOA Energy Savings Percent** (CT-SOA)/ (CT-TM)
Glass Fiber Production (glass fibers)				
Batching	0.25	0.19	0.06	22.3%
Melting	2.54	1.50	1.04	47.3%
Fiberization	0.55	0.46	0.10	10.8%
Finishing	0.55	0.49	0.06	11.7%
Resin Production* (matrix polymer)	25.24	20.19	5.05	19.9%
Composite Product Forming** (composite product)	1.61	1.29	0.32	20.0%
Total***	30.75	24.12	6.63	21.5%

Current Typical (CT), State of the Art (SOA), Thermodynamic Minimum (TM)

* SOA energy savings is also called *Current Opportunity*.

** SOA energy savings percent is the SOA energy savings opportunity from transforming glass fiber composite production processes through the adoption of state of the art equipment and practices. Energy savings percent is calculated using the TM energy consumption shown in Table 6-4 as the minimum energy consumption. The energy savings percent, with TM as the minimum, is calculated as follows: SOA Energy Savings Percent = (CT-SOA)/(CT-TM)

***Note: totals may not sum due to independent rounding.

If all U.S. glass fiber, resin, and composites producers (based on the 2010 production level of GFRP composites for application areas considered) were able to attain SOA energy intensities, it is estimated that a total of 6.6 TBtu of on-site energy could be saved annually, corresponding to a 21.5% energy savings overall. This energy savings estimate is based on adopting available SOA technologies and practices without accounting for future gains in energy efficiency from R&D. This is a simple estimate for potential savings; not all existing plants could necessarily achieve these state of the art values. No assessment was made in this study regarding whether the improvements would prove to be cost effective in all cases.

5. Practical Minimum Energy Intensity and Energy Consumption

Technology innovation is the driving force for economic growth. Across the globe, R&D is underway to make GFRP composites in new ways, improving energy efficiency as well as composite performance. Commercialization of these improvements will drive the competitiveness of U.S. GFRP composites manufacturing. In this chapter, the energy savings possible through R&D advancements in GFRP composites manufacturing are estimated. Practical minimum (PM) is the minimum amount of energy required assuming the successful deployment of applied R&D technologies under development worldwide.

5.1. Practical Minimum Energy Intensity

R&D progress is difficult to predict, and the realization of potential gains in energy efficiency can depend on financial investments and market priorities. To estimate PM energy consumption for this bandwidth analysis, a review of R&D activities in glass fiber manufacturing, polymer resin manufacturing, and composites production techniques was conducted. The focus of this search was applied research, defined as the investigation and development of new technologies with the intent of accomplishing a particular commercial objective. Basic science research, involving experimentation and modeling to expand understanding of fundamental mechanisms and principles without a direct link to commercial objectives, was not considered. Further, applied R&D technologies without a clear connection to manufacturing energy consumption (improved damage detection or multi-material joining techniques, for example) were not considered in this study.

PM energy intensity was estimated for glass fibers by applying assumed energy savings percentages for applicable PM technologies to the baseline SOA energy intensities for each manufacturing sub-process. The PM technologies included in this analysis and assumed energy savings were:

- **Aggressive glass fiber recycling:** 24% savings in fiber production processes
- **New grinding technologies:** 5% savings in the batching process
- **More efficient forehearths or oxygen-gas-fired forehearths:** 12% savings in the melting process
- **Improved fiber curing and drying:** 30% savings in the finishing process
- **Process integration/pinch analysis:** 4% savings across all processes (cross-cutting technology).

The energy savings from the PM technologies essentially “stack” with the SOA technologies described earlier, and are not double-counted in the analysis. For a discussion of these energy savings estimates and sources, see Appendix A4. Appendix A4 also provides details of additional technologies that were considered but not included in the final PM model. The excluded technologies were considered incompatible with PM technologies already included in the model. Table 5-1 presents the estimated PM energy intensities for glass fibers.

Table 5-1. Practical Minimum Energy Intensity for Production of Glass Fibers

Glass Fiber Production Sub-Process	On-site PM Energy Intensity (Btu/lb)	Primary* PM Energy Intensity (Btu/lb)	Data Source
Batching	183	567	Calculated; see Appendix A4 for sources
Melting	1,432	1,462	Rue (2007)
Fiberization	398	615	Calculated; see Appendix A4 for sources
Finishing	338	374	Calculated; see Appendix A4 for sources
Total Energy Intensity for Glass Fibers	2,351	3,017	

Practical Minimum (PM)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

** Note: totals may not sum due to independent rounding.

For resin manufacturing and composite product forming processes, PM energy intensity was again estimated by applying assumed energy savings percentages for applicable PM technologies to the baseline SOA energy intensities for each sub-process. The PM technologies and assumed energy savings were:

For resin manufacturing:

- **Plastics recycling and recovery:** 49% savings for thermoplastic resins and 35% savings for thermosetting resins
- **Process integration/pinch analysis:** 4% savings across all processes (cross-cutting technology).

For composite product forming:

- **Barrel insulation to reduce thermal losses:** 10% savings for injection molding, resin transfer molding, and vacuum-assisted resin infusion
- **Infrared heating with emissivity matching:** 50% savings for pultrusion and thermoforming;
- **Improved die design:** 5% savings for pultrusion
- **Process integration/pinch analysis:** 4% savings across all processes (cross-cutting technology).

For a discussion of these technologies and energy savings estimates, including references, see Appendix A4. Table 5-2 and Table 5-3 present the estimated PM energy intensities for the six matrix polymer materials and the twelve composites production techniques studied, respectively.

Table 5-2. Practical Minimum Energy Intensity for Production of Matrix Resins

Matrix Polymer	On-site PM Energy Intensity (Btu/lb)	Primary* PM Energy Intensity (Btu/lb)	Data Source
Thermosetting Resins			
Epoxy resin	17,101	20,021	Calculated; see Appendix A4 for sources
Polyurethane resin	5,690	13,655	Calculated; see Appendix A4 for sources
Thermoplastic Resins			
Polypropylene (PP)	2,047	4,631	Calculated; see Appendix A4 for sources
High density polyethylene (HDPE)	2,184	4,664	Calculated; see Appendix A4 for sources
Polyvinyl chloride (PVC)	3,264	5,439	Calculated; see Appendix A4 for sources
Polystyrene (PS)	4,039	6,799	Calculated; see Appendix A4 for sources

Practical Minimum (PM)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

Table 5-3. Practical Minimum Energy Intensity for Composite Product Forming

Production Method	On-site PM Energy Intensity (Btu/lb)	Primary* PM Energy Intensity (Btu/lb)	Data Source
Intermediate (Semi-finished) Manufacturing Methods			
Prepreg	13,207	40,887	Calculated; see Appendix A4 for sources
Sheet or bulk molding compound	1,156	3,578	Calculated; see Appendix A4 for sources
Direct Forming Methods			
Open molding (hand lay-up or spray up)	1,628	3,366	Calculated; see Appendix A4 for sources
Filament winding	891	2,760	Calculated; see Appendix A4 for sources
Pultrusion	486	1,505	Calculated; see Appendix A4 for sources
Injection molding	799	2,474	Calculated; see Appendix A4 for sources
Compression molding	2,021	5,983	Calculated; see Appendix A4 for sources
Resin transfer molding (including vacuum infusion)	755	1,392	Calculated; see Appendix A4 for sources
Thermoforming	4,243	13,031	Calculated; see Appendix A4 for sources
Cold press	3,896	12,062	Calculated; see Appendix A4 for sources

Practical Minimum (PM)

* Primary energy accounts for off-site electricity generation and transmission losses, assuming a grid efficiency of 32.3%. Process-specific energy mix data were used to determine the ratio of fuel and electricity consumed on-site. See Appendix A3 for energy mix assumptions.

5.2. Practical Minimum Energy Consumption

Table 5-4 presents the calculated on-site and primary PM energy consumption for the GFRP production subareas studied. In these summary data, epoxy resin was assumed as the polymer matrix material and resin transfer molding was assumed as the composite product forming method. Energy consumption values were calculated by multiplying energy intensity (Btu/lb) by 2010 production (lbs). On-site energy intensities were converted to primary (and vice versa) using process-specific energy mix data, as described in Appendix 3.

Table 5-4. Calculated Practical Minimum Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied

Subarea (product)	On-site PM Energy Intensity (Btu/lb)	Primary PM Energy Intensity (Btu/lb)	Production (million lbs)	On-site PM Energy Consumption (TBtu/yr)	Off-site Losses, Calculated (TBtu/yr)	Primary PM Energy Consumption (TBtu/yr)
Glass Fiber Production (glass fibers)						
Batching	183	567	737	0.13	0.28	0.42
Melting	1,432	1,462	737	1.05	0.02	1.08
Fiberization	398	615	737	0.29	0.16	0.45
Finishing	338	374	737	0.25	0.03	0.28
Resin Production* (matrix polymer)	17,101	20,021	737	12.60	2.15	14.75
Composite Product Forming** (composite product)	755	1,392	1,473	1.11	0.94	2.05
Total***				15.44	3.58	19.02

Practical Minimum (PM)

* Assumes thermosetting epoxy resin

** Assumes resin transfer molding

***Note: totals may not sum due to independent rounding.

Table 5-5 presents a comparison of the on-site CT energy consumption and PM energy consumption for each process subarea and as a total. The difference between the CT and PM energy consumption values is presented as the PM energy savings (or the sum of the *Current Opportunity* plus the *R&D Opportunity*). Table 5-6 calculates the R&D opportunity for the process subareas studied.

Among the processes studied, the greatest *current plus R&D opportunity* in terms of percent energy savings is glass melting at 67.6% energy savings. The greatest *current plus R&D opportunity* in terms of TBtu savings was resin production at 12.64 TBtu per year savings.

If all U.S. glass fiber, resin, and composites producers (based on the 2010 production level of GFRP composites for application areas considered) were able to attain PM energy intensities, it is estimated that a total of 15.02 TBtu of on-site energy could be saved annually, corresponding to an 48.7% energy savings overall. This energy savings estimate assumes the adoption of the PM technologies and practices described in this report. This is a simple estimate for potential savings, as the PM technologies considered are unproven, and not all existing plants could necessarily deploy all of the practices considered. No assessment was made in this study regarding whether the improvements would prove to be cost effective in all cases, nor whether satisfactory GFRP performance could be achieved via the PM processes.

Table 5-5. Calculated Practical Minimum Energy Savings for Glass Fiber Composite Manufacturing: Application Areas Studied

Subarea (product)	On-site CT Energy Consumption, Calculated (TBtu/yr)	On-site PM Energy Consumption, Calculated (TBtu/yr)	PM Energy Savings* (CT - PM) (TBtu/yr)	PM Energy Savings Percent** (CT-PM)/(CT-TM)
Glass Fiber Production (glass fibers)				
Batching	0.25	0.13	0.12	46.2%
Melting	2.54	1.05	1.49	67.6%
Fiberization	0.55	0.29	0.26	29.0%
Finishing	0.55	0.25	0.30	54.9%
Resin Production* (matrix polymer)	25.24	12.60	12.64	49.9%
Composite Product Forming** (composite product)	1.61	1.11	0.50	30.9%
Total***	30.75	15.44	15.30	49.6%

Current Typical (CT), Practical Minimum (PM), Thermodynamic Minimum (TM)

* PM energy savings is the Current Opportunity plus the R&D Opportunity.

** PM energy savings percent is the PM energy savings opportunity from transforming glass fiber composite production processes through the adoption of state of the art equipment and practices. Energy savings percent is calculated using the TM energy consumption shown in Table 6-4 as the minimum energy consumption. The energy savings percent, with TM as the minimum, is calculated as follows: PM Energy Savings Percent = (Current-PM)/(Current-TM)

***Note: totals may not sum due to independent rounding.

The R&D savings percent is the percent of energy saved with SOA energy consumption compared to CT energy consumption. The PM energy savings percent in Table 5-5 is the percent of energy saved with PM energy consumption compared to CT energy consumption, while referencing the thermodynamic minimum as the baseline energy consumption. Thermodynamic minimum (TM), discussed further in the following section, is considered to be equal to zero in an ideal case with perfect efficiency (i.e., energy input to a system is considered fully recoverable with no friction losses or change in surface energy). For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical reaction or permanent crystalline change due to deformation), TM is not necessarily equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0). Referencing TM as the baseline in comparing bandwidths of energy consumption and calculating energy savings percent provides the most accurate measure of absolute savings potential. The equation for calculating on-site R&D opportunity and PM energy savings percent are:

$$R\&D\ Opportunity\ \% = \frac{SOA - PM}{CT - TM}$$

$$PM\ Savings\ \% = \frac{CT - PM}{CT - TM}$$

R&D opportunity represents the opportunities for energy savings from technologies currently an R&D stage of development (early TRL) and are not ready for deployment to manufacturing. It represents the energy savings opportunities that can be achieved if the R&D is put into those technologies to get them to a high enough TRL level that they can be deployed in the manufacturing sector. Table 5-6 shows the R&D opportunity totals and percent for the evaluated process subareas.

Table 5-6. Calculated Practical Minimum Energy Consumption, R&D Opportunity, and R&D Opportunity Percent for Glass Fiber Composite Manufacturing: Application Areas Studied

Subarea	On-site SOA Energy Consumption (TBtu/year)	On-site PM Energy Consumption (TBtu/year)	R&D Opportunity (SOA-PM) (TBtu/year)	R&D Opportunity Savings Percent* (SOA-PM)/(CT-TM)
Total for Process Subareas Studied	24.12	15.44	8.68	28.1%

Current Typical (CT), State of the Art (SOA), Practical Minimum (PM), Thermodynamic Minimum (TM)

* Energy savings percent is calculated using TM energy consumption shown in Chapter 6 as the minimum energy consumption. The energy savings percent, with TM as the minimum, is calculated as follows: (SOA- PM)/(CT- TM).

6. Thermodynamic Minimum Energy Intensity and Energy Consumption

Real-world manufacturing does not occur under theoretically ideal conditions; however, understanding the theoretical minimal amount of energy required to manufacture GFRP composites can provide a more complete understanding of the realistic opportunities for energy savings. This baseline can be used to establish more realistic projections (and bounds) for the future R&D energy savings that may be achieved. This chapter presents the thermodynamic minimum (TM) energy consumption required for the subareas studied.

TM energy consumption, which is based on Gibbs free energy calculations, assumes ideal conditions that are unachievable in real-world applications. TM energy consumption assumes that all energy is used productively, that there are no energy losses, and that energy is ultimately perfectly conserved by the system (i.e., when cooling a material to room temperature or applying work to a process, the heat or work energy is fully recovered – perfect efficiency¹⁹). It is not anticipated that any manufacturing process would ever attain this value in practice. A reasonable long-term goal for energy efficiency would be the practical minimum (see Chapter 5).

For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical reaction or permanent crystalline change due to deformation), TM is not necessarily equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0).

6.1. Thermodynamic Minimum Energy Intensity

The thermodynamic minimum energy intensity was calculated for each sub-process by determining the Gibbs free energy associated with the chemical transformations involved, under ideal conditions for a manufacturing process.²⁰ The TM energy intensity is *negative* when the chemical reaction is net-exergonic and *positive* when the chemical reaction is net-endergonic.²¹ Changes in surface energy were not considered in the TM analysis. The change in entropy was calculated based on the relative change in the number of molecules, and the change in enthalpy was calculated based on the change in bond energy.²²

TM energy intensity calculations are process path independent (state function), but are directly related to the relative energy levels of the substrate reactants and the products. The reported value depends only on the starting material and the end product, and would not change if the process had greater or fewer process steps or if a catalyst were involved. For polymerization reactions, the starting material is assumed to be the relevant monomers (not crude petroleum). It is important to note that a negative TM value does not imply that the reaction will occur without being forced by a manufacturing process.

In this report, TM energy consumption is referenced as the baseline (or minimum amount of energy) when calculating the absolute energy savings potential. The equations used to determine the absolute energy savings for current opportunity (SOA), R&D, and PM are defined below. PM savings percent is the sum of the current opportunity percent and the R&D opportunity percent.

$$\text{Current opportunity \%} = \frac{CT - SOA}{CT - TM}$$

¹⁹ It is noted that other authors have calculated theoretical minimum energy consumption by assuming that thermal energy *cannot* be recovered from the product itself (see e.g., Levine 2007). Since it is theoretically possible to recover such energy, this analysis assumes that all such energy can be recovered.

²⁰ Unless otherwise noted, “ideal conditions” means a pressure of 1 atmosphere and a temperature of 77°F.

²¹ Exergonic (reaction is favorable) and endergonic (reaction is not favorable) are thermodynamic terms describing the total change in Gibbs free energy (delta G). This differs from exothermic (reaction is favorable) and endothermic (reaction is not favorable) terminology that are used in describing change in enthalpy (delta H).

²² Note that the bond energy values are averages, not specific to the molecule in question.

$$R\&D \text{ opportunity } \% = \frac{SOA - PM}{CT - TM}$$

$$PM \text{ Savings } \% = \frac{CT - PM}{CT - TM}$$

For processes requiring an energy intensive transformation (e.g., melting), this percent energy savings approach results more realistic and comparable energy savings estimates. Using zero as the baseline (or minimum amount of energy) would exaggerate the total bandwidth to which SOA energy savings and PM energy savings are compared to determine the energy savings percent. When TM energy consumption is referenced as the baseline, SOA energy savings and PM energy savings are relatively more comparable, resulting in more accurate energy savings percentages.

For glass fiber manufacturing, only the melting and fiberization processes had nonzero TM energy intensities. The TM energy for these processes was estimated on the basis of a constant heat capacity.²³ Values are presented in Table 6-1. Note that primary energy intensity was not calculated for TM because energy conversion is assumed to be perfect in the theoretical minimum case.

Table 6-1. Thermodynamic Minimum Energy Intensity for Production of Glass Fibers

Glass Fiber Production Sub-Process	On-site TM Energy Intensity (Btu/lb)	Data Source
Batching	0	n/a
Melting	465	Calculated*
Fiberization	-465	Calculated*
Finishing	0	n/a
Total Energy Intensity for Glass Fibers	0	

Thermodynamic Minimum (TM)

*See preceding discussion in text for description of methodology.

The TM energy intensity values for the matrix polymers reflect polymerization of the resin from its monomers, assuming a polymer chain 1000 repeat units in length.²⁴ TM values for the polymer materials are presented in Table 6-2. For composite product forming there is no change to the embodied free energy content of the materials being produced, no chemical reactions or phase changes are involved in the processes; the TM energy intensity was therefore assumed to be zero for all methods, as shown in Table 6-3.

²³ During the melting phase, glass is heated from room temperature to 1370°C; during the fiberization phase, the molten glass is cooled back to room temperature (Wallenberger (2001)). Given a heat capacity of 0.345 Btu/lb°C for the glass, the TM energy intensity for melting is 465 Btu/lb and for fiberization is -465 Btu/lb [the opposite].

²⁴ The exception was epoxy, which is based upon a chain consisting of 25 units of bisphenol-A and 26 units of epichlorohydrin.

Table 6-2. Thermodynamic Minimum Energy Intensity for Production of Matrix Resins

Matrix Polymer	On-site TM Energy Intensity (Btu/lb)	Data Source
Thermosetting Resins		
Epoxy resin	-115	Calculated*
Polyurethane resin	-188	Calculated*
Thermoplastic Resins		
Polypropylene (PP)	-1,163	Calculated*
High density polyethylene (HDPE)	-1,744	Calculated*
Polyvinyl chloride (PVC)	-969	Calculated*
Polystyrene (PS)	-470	Calculated*

Thermodynamic Minimum (TM)

* Calculated based on polymerization of the resin from its monomers; see discussion in text for details of methodology used.

Table 6-3. Thermodynamic Minimum Energy Intensity for Composite Product Forming

Production Method	On-site TM Energy Intensity (Btu/lb)	Data Source
Intermediate (Semi-finished) Manufacturing Methods		
Prepreg	0	Best engineering judgment*
Sheet or bulk molding compound	0	Best engineering judgment*
Direct Forming Methods		
Open molding (hand lay-up or spray up)	0	Best engineering judgment*
Spray up	0	Best engineering judgment*
Filament winding	0	Best engineering judgment*
Pultrusion	0	Best engineering judgment*
Injection molding	0	Best engineering judgment*
Compression molding	0	Best engineering judgment*
Resin transfer molding (including vacuum infusion)	0	Best engineering judgment*
Thermoforming	0	Best engineering judgment*
Cold press	0	Best engineering judgment*

Thermodynamic Minimum (TM)

*See discussion in text for details of methodology used.

6.2. Thermodynamic Minimum Energy Consumption

Table 6-4 presents the calculated TM energy consumption for the GFRP production subareas studied. In these summary data, epoxy resin was assumed as the polymer matrix material and resin transfer molding was assumed as the composite product forming method. Energy consumption values were calculated by multiplying energy intensity (Btu/lb) by the 2010 production volume (lbs).

Table 6-4. Calculated Thermodynamic Minimum Energy Consumption for Glass Fiber Reinforced Polymer Composite Manufacturing: Application Areas Studied

Subarea (product)	TM Energy Intensity (Btu/lb)	Production (million lbs)	TM Energy Consumption (TBtu/yr)
Glass Fiber Production (glass fibers)			
Batching	0	737	0
Melting	465	737	0.34
Fiberization	-465	737	-0.34
Finishing	0	737	0
Resin Production* (matrix polymer)	-115	737	-0.08
Composite Product Forming** (composite product)	0	1,473	0
Total***			-0.08

Thermodynamic Minimum (TM)

* Assumes thermosetting epoxy resin.

** Assumes resin transfer molding.

***Note: totals may not sum due to independent rounding.

7. Current and R&D Opportunity Analysis/Bandwidth Summary

Table 7-1 summarizes the *current opportunity* and *R&D opportunity* energy savings for the subareas studied, based on GFRP composite production in 2010 for the four boundary application areas. Glass fiber production is broken down into its four sub-processes. The savings total reflects a representative composite formulation, with epoxy resin assumed as the polymer matrix material, a 50% fiber fraction (by weight), and resin transfer molding assumed as the forming method, as shown in Table 7-2. Readers wishing to estimate energy savings opportunities for other composite material formulations may do so by substituting data for other resins and forming methods (as presented in this report) in a mix-and-match fashion.

Table 7-1. Current and R&D Opportunities for GFRP Manufacturing (On-site Energy Consumption): Application Areas Studied

Subarea (product)	Current Energy Savings Opportunity (CT – SOA) (TBtu/year)	R&D Energy Savings Opportunity (SOA – PM) (TBtu/year)
Glass Fiber Production (glass fibers)		
Batching	0.06	0.06
Melting	1.04	0.45
Fiberization	0.10	0.16
Finishing	0.06	0.24
Resin Production – epoxy resin (matrix polymer)	5.05	7.59
Composite Product Forming – resin transfer molding (composite product)	0.32	0.18
Total*	6.63	8.68

Current typical (CT), state of the art (SOA), practical minimum (PM)

* Note: totals may not sum due to independent rounding.

Table 7-2. Manufacturing Process Assumptions for Current Typical, State of the Art, and Practical Minimum Energy Bands

Energy Band	Fiber Fraction (weight %)	Polymer Matrix Material	Composite Production Method
Current Typical	50%	Epoxy resin	Resin transfer molding
State of the Art	50%	Epoxy resin	Resin transfer molding
Practical Minimum	50%	Epoxy resin	Resin transfer molding
Thermodynamic Minimum	50%	Epoxy resin	Resin transfer molding

In this study, two hypothetical opportunity bandwidths for energy savings were estimated (as defined in Chapter 1). The analysis shows the following:

- *Current Opportunity* – 6.63 TBtu per year of on-site energy savings could be realized if state of the art technologies and practices are deployed
- *R&D Opportunity* – 8.68 TBtu per year of additional on-site energy savings could be attained in the future if applied R&D technologies under development worldwide are successfully deployed (i.e., reaching the practical minimum).

Figure 7-1 depicts these two opportunity bandwidths graphically. The area between *R&D opportunity* and *impractical* is shown as a dashed line with color fading because the PM energy savings impacts are based on today's knowledge of research tested between laboratory and demonstration scale; emerging technologies being investigated through modeling and theoretical calculations may eventually bring the PM energy consumption further into the faded region and closer to the TM energy consumption. The *impractical* bandwidth, or the difference between the PM and TM energy consumption, represents the area that would require fundamental changes in GFRP manufacturing. The term *impractical* is used because the PM energy consumption is based on current knowledge of R&D technologies tested between laboratory and demonstration scale; further decreases in energy intensity have not been displayed at any physical scale.

Based on the bandwidth analysis, the greatest *current* and *R&D* energy savings opportunities could be achieved by upgrading resin production techniques. Examples of technologies that could be deployed to achieve these opportunities were detailed in this report and its appendices.

It is noted that this report assumes the same composite formulation (an epoxy resin matrix, a 50% fiber fraction by weight, and resin transfer molding) in all summary calculations to ensure comparability between the energy bands presented. Additional energy savings could be achieved by altering these parameters. Polymer materials and composite forming techniques vary widely in energy intensity, and substituting one material or method for another alters the energy intensity of a composite. While major energy savings are potentially available from these types of changes, the reader is cautioned that the resulting composite products may not be comparable on a performance basis. Careful attention to application-specific component design and requirements is needed to understand these additional potential energy savings opportunities.




Figure 7-1. Current and R&D energy savings opportunities (on-site energy consumption) for GFRP composite manufacturing by process, based on 2010 glass fiber production for structural applications
Source: EERE

8. References

- ACC (2011) American Chemistry Council (2011), "Cradle-to-Gate Life Cycle Inventory of Nine Plastic Resins and Four Polyurethane Precursors," prepared by Franklin Associates for the Plastics Division of the American Chemistry Council.
- ACS (1993) The American Ceramic Society, 53rd Conference on Glass Problems: Ceramic Engineering & Science Proceedings, March-April 1993.
- Adasan (2016) Adasen Machinery Co. website. "Microwave dryer machine/Microwave glass fiber drying equipment." Available at: <http://www.dryersterilizer.com/content/?342.html>
- Beerkens (2011) Beerkens, R. (2011), "Concepts for Energy & Emission Friendly Glass Melting: Evolution or Revolution in Glass Melting," presented at the 9th International Conference on Advances in Fusion and Processing of Glass, July 11-14, Cairns, Australia, available from: <http://publications.tno.nl/publication/100347/EAHeqQ/beerkens-2012-new.pdf>
- Das (2011) Das S. (2011), "Life Cycle Assessment of Carbon Fiber-Reinforced Polymer Composites," Int. Journal of Life Cycle Assessment 16, pp. 268-282
- DOE (2014) Clean Energy Manufacturing Innovation Institute for Composite Materials and Structures. Funding Opportunity Announcement (FOA) Number DE-FOA-0000977. DOE/EERE. 2014. <https://energy.gov/eere/amo/articles/clean-energy-manufacturing-innovation-institute-composites-materials-and>
- Duflou (2009) Duflou J.R., DeMoor J., Verpoest I., and Dewulf W. (2009), "Environmental Impact analysis of composite use in car manufacturing," CIRP Annals – Manufacturing Technology 58, pp. 9-12
- EIA (2016) U.S. Energy Information Administration. (2016), "November 2016 Monthly Energy Review," Table 2.4: Industrial Sector Energy Consumption. Released November 22, 2016.
- Energetics (2015a) Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Petroleum Refining. Prepared by Energetics Inc. for the U.S. DOE Advanced Manufacturing Office. 2015. <http://www.energy.gov/eere/amo/downloads/bandwidth-study-energy-use-and-potential-energy-saving-opportunities-us-petroleum>
- Energetics (2015b) Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Chemical Manufacturing. Prepared by Energetics Inc. for the U.S. DOE Advanced Manufacturing Office. 2015. <http://www.energy.gov/eere/amo/downloads/bandwidth-study-energy-use-and-potential-energy-saving-opportunities-us-chemical>
- Energetics (2015c) Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Iron and Steel Manufacturing. Prepared by Energetics Inc. for the U.S. DOE Advanced Manufacturing Office. 2015. <http://www.energy.gov/eere/amo/downloads/bandwidth-study-energy-use-and-potential-energy-saving-opportunities-us-iron-and>

- Energetics (2015d) Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Pulp and Paper Manufacturing. Prepared by Energetics Inc. for the U.S. DOE Advanced Manufacturing Office. 2015. <http://www.energy.gov/eere/amo/downloads/bandwidth-study-energy-use-and-potential-energy-saving-opportunities-us-pulp-and>
- Franklin (2011) Franklin Associates. (2011), "LCI of Plastic Fabrication Processes."
- Gardiner (2014) Gardiner, G. (2014), "Recycled carbon fiber update: closing the CFRP lifecycle loop," Composites World, 11/30/2014
- Hains (2009) Hains, D.H, London I.M., and Merivale C.A. (2009), "Batch solutions to reduce energy demand and carbon footprint in glassmaking," Avalon Rare Metals Inc.
- Hopewell (2009) Hopewell J., Dvorak R. and Kosior E. (2009), "Plastics recycling: challenges and opportunities," Philosophical Transactions of the Royal Society B 364, pp. 2115-2126
- Jacob (2005) Jacob G.C., Starbuck J.M., Fellers J.F., and Simunovic S. (2005), "Effect of fiber volume fraction, fiber length, and fiber tow size on the energy absorption of chopped carbon fiber-polymer composites," Polymer Composites 26, pp. 293-305
- JEC (2011) JEC (2011), "Global glass-fibre production: changes across the board" JEC Group News, posted 21 February 2011, available from: <http://www.jeccomposites.com/knowledge/international-composites-news/global-glass-fibre-production-changes-across-board>
- JEC (2012) JEC (2012), JEC Americas 2012: "The American Composites Market."
- Kim (2014) Kim, S. "Engineering sustainability of mechanical recycling of carbon fiber composite materials," Undergraduate Research Opportunities Program Paper, University of Minnesota - Duluth.
- Krause (2008) Krause F.L. (2008), "Energy Efficiency in Manufacturing: The Role of ICT," Report of the European Commission Smart Manufacturing Consultation Group.
- Levine (2007) Levine, E., Jamison, K., Rue, D., and Wolf, W., "Advancing energy efficiency in the U.S. glass industry: perspective from the DOE Industrial Technologies Program," paper presented at the 2007 ACEEE Summer Study on Energy Efficiency in Industry, available from: http://aceee.org/files/proceedings/2007/data/papers/74_6_121.pdf
- Linde (2016) Linde "Flexibility meets efficiency. CGM™ and oxy-fuel for fiberglass production." pg. 9. http://www.glass-strand.com/26098_Fiberglas_Brochure_Vers2.pdf
- Martin (2000) Martin et al, "Emerging Energy-Efficient Industrial Technologies," Lawrence Berkeley National Laboratory (2000)
- MFI (2016) Data from the NREL "Materials Flow through Industry" tool database, provided by Dr. Rebecca Hanes (NREL), November 2016.

- Pellegrino (2002) Pellegrino, J., "Glass Industry of the Future: Energy and Environmental Profile of the U.S. Glass Industry," prepared by Energetics Incorporated for the U.S. DOE Office of Industrial Technologies, April 2002, available from:
<http://www.nrel.gov/docs/fy02osti/32135.pdf>
- PlasticsEurope (2005a) Eco-Profiles of the European Plastics Industry: Polyurethane Rigid Foam. PlasticsEurope. 2005. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- PlasticsEurope (2005b) Eco-Profiles of the European Plastics Industry: Polyvinyl Chloride (PVC) (Bulk Polymerization). PlasticsEurope. 2005. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- PlasticsEurope (2006) Eco-Profiles of the European Plastics Industry: Liquid Epoxy Resins. PlasticsEurope. 2006. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- PlasticsEurope (2012) Eco-Profiles and Environmental Product Declarations of the European Plastics Manufacturers: General-Purpose Polystyrene and High-Impact Polystyrene. PlasticsEurope. 2012. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- PlasticsEurope (2014a) Eco-Profiles and Environmental Product Declarations of the European Plastics Manufacturers: Polypropylene (PP). PlasticsEurope. 2014. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- PlasticsEurope (2014b) Eco-Profiles and Environmental Product Declarations of the European Plastics Manufacturers: High-Density Polyethylene (HDPE), Low-Density Polyethylene (LDPE), Linear Low-Density Polyethylene (LLDPE). PlasticsEurope. 2014. <http://www.plasticseurope.org/plastics-sustainability-14017/eco-profiles.aspx>
- Praxair (2016) Praxair "DOC-Forehearth Oxy-Fuel Burner (DOC-FH) <http://www.praxair.com/-/media/documents/specification-sheets-and-brochures/industries/glass/p102615-docfh-burner.pdf>
- Rocky Mountain Institute (2013) Rocky Mountain Institute (2013). Autocomposites Workshop Report. *Kickstarting the Widespread Adoption of Automotive Carbon Fiber Composites: Key Findings & Next Steps*, January 2013.
- Rue (2007) Rue, D.M.; Servaites, J.; Wolf, W. (2007), "Final Report: Industrial Glass Bandwidth Analysis," prepared by Gas Technology Institute for the U.S. Department of Energy, available from:
https://www.energy.gov/sites/prod/files/2013/11/f4/industrial_bandwidth.pdf
- Scalet (2013) Scalet, B. M. e.t., a.l. 2013 "Best Available Techniques (BAT) Reference Document for the Manufacture of Glass" European Commission

Joint Research Centre Institute for prospective technological studies, available from:
http://eippcb.jrc.ec.europa.eu/reference/BREF/GLS_Adopted_03_2012.pdf
- Schepp (2006) Schepp, C. et al. (2006), "Plastics Industry Energy Best Practice Guidebook," Focus on Energy.

- Sommariv (2015) Sommariv, L., Weinberger K. "Energy and Natural Resources Saving in the Production of Expanded Glass Granules" 2015. Available from <http://www.aidic.it/icheap12/168sommariva.pdf>
- Stalam (2016) Stalam website "Dryers for glass fibres" available at: <http://www.stalam.com/en/rf-dryers-for-glass-fibres.html>
- Stiller (1999) Stiller, H. (1999), "Material intensity of advanced composite materials," prepared by Wuppertal Institute for the Verbundwerkstofflabor Bremen, February 1999, available from: <http://epub.wupperinst.org/files/926/WP90.pdf>
- Suzuki & Takahashi (2005) Suzuki T. and Takahashi J. (2005), "Prediction of Energy Intensity of Carbon Fiber Reinforced Plastics for Mass-Produced Passenger Cars," 9th Japan International SAMPE Symposium, Nov. 29-Dec. 2, 2005.
- Thiriez (2006) Thiriez A. and Gutowski T. (2006), "An environmental analysis of injection molding," Proceedings of the 2006 ISEE International Symposium on Electronics and the Environment
- USLCI (2012) National Renewable Energy Laboratory U.S. Life Cycle Inventory Database, available online from: <https://uslci.lcacommons.gov/uslci/search>
- Wallenberger (2001) Wallenberger F.T., Watson J.C., and Li H. (2001), *Glass Fibers*, ASM Handbook, Vol. 2: Composites.
- Worrell (2008) Worrell E., Galitsky C., Masanet E., and Graus W. (2008), "Energy Efficiency Improvement and Cost Saving Opportunities for the Glass Industry," LBNL/EPA
- Worrell (2010) Worrell E., Angelini T., and Masanet E. (2010), *Managing Your Energy: An ENERGY STAR Guide for Identifying Energy Savings in Manufacturing Plants*, LBNL/EPA, LBNL Report No. 3714E.
- Yang (2012) Yang Y. et al. (2012), "Recycling of composite materials," *Chemical Engineering and Processing: Process Intensification* 51, pp. 53-68

Appendix A1. Master GFRP Composite Summary Tables

Table A1-1. On-site Energy Intensity and Energy Consumption Estimates for GFRP Composite Manufacturing for the Four Bandwidth Measures, Based on 2010 Production of GFRP Composites for Structural Application Areas

Process Subarea or Sub-Process	2010 Application Area Production* (million lbs)	Estimated On-site Energy Intensity** (Btu/lb)				Calculated On-site Energy Consumption (TBtu/yr)			
		CT	SOA	PM	TM	CT	SOA	PM	TM
Glass Fiber Production									
Batching	737	340	264	183	0	0.25	0.19	0.13	0.00
Melting		3,450	2,039	1,432	465	2.54	1.50	1.05	0.34
Fiberization		751	619	398	-465	0.55	0.46	0.29	-0.34
Finishing		751	663	338	0	0.55	0.49	0.25	0.00
Overall - Fiber Production		5,292	3,586	2,351	0	3.90	2.64	1.73	0.00
Resin Production									
Epoxy resin	737	34,256	27,405	17,101	-115	25.24	20.19	12.60	-0.08
Polyurethane resin		11,398	9,118	5,690	-188	8.40	6.72	4.19	-0.14
Polypropylene (PP)		5,227	4,182	2,047	-1163	3.85	3.08	1.51	-0.86
High density polyethylene (HDPE)		6,845	4,461	2,184	-1744	5.04	3.29	1.61	-1.28
Polyvinyl chloride (PVC)		9,158	6,666	3,264	-969	6.75	4.91	2.40	-0.71
Polystyrene (PS)		10,751	8,249	4,039	-470	7.92	6.08	2.98	-0.35
Composite Product Forming									
Prepreg	1,473	17,196	13,757	13,207	0	25.34	20.27	19.46	0.00
Sheet or bulk molding compound		1,505	1,204	1,156	0	2.22	1.77	1.70	0.00
Open molding (hand lay-up or spray up)		2,237	1,696	1,628	0	3.30	2.50	2.40	0.00
Filament winding		1,161	929	891	0	1.71	1.37	1.31	0.00
Pultrusion		1,333	1,066	486	0	1.96	1.57	0.72	0.00
Injection molding		2,794	925	799	0	4.12	1.36	1.18	0.00
Compression molding		2,632	2,106	2,021	0	3.88	3.10	2.98	0.00
Resin transfer molding (including vacuum infusion)		1,093	874	755	0	1.61	1.29	1.11	0.00
Thermoforming		11,048	8,839	4,243	0	16.28	13.02	6.25	0.00
Cold press		5,073	4,058	3,896	0	7.47	5.98	5.74	0.00
Total for Glass Fiber Reinforced Polymer Manufacturing***		1,473	20,866	16,369	10,481	-58	30.75	24.12	15.44

* Glass fiber production data reflect the total production of finished fibers used in automotive, wind energy, pressure vessel, and aerospace applications. Resin production data indicate the estimated production of all resins for GFRP composites in the application areas, assuming 50 wt% glass fibers. Composites production indicates the total production of GFRP composites (all methods) calculated from the above data.

** Energy intensities reported in terms of Btu per pound of fibers for glass fiber production (all sub-processes), Btu per pound of resin for resin production, and Btu per pound of composite product (fibers and resin) for composites production. The total energy intensity for GFRP composites is reported in Btu per pound of composite product. Feedstock energy is excluded in all values.

*** Total is a representative value assuming a fiber fraction of 50 wt% glass fibers (the median value in seven automotive case studies considered; see Appendix A2). The polymer material was assumed to be the product forming method was assumed to be resin transfer molding. The values included in the total are shown in bold in the table. The formula used for the calculation was: Total GFRP Energy = (0.50*[Fiber

Production Energy] + 0.50*[Resin Production Energy] + Product Forming Energy). To determine the total for another GFRP composition, the material-specific energy intensity can be calculated by substituting other table values in this formula.

Table A1-2. Primary Energy Intensity and Energy Consumption Estimates for GFRP Composite Manufacturing for the Four Bandwidth Measures, Based on 2010 Production of GFRP Composites for Structural Application Areas

Process Subarea or Sub-Process	2010 Application Area Production* (million lbs)	Estimated Primary Energy Intensity** (Btu/lb)				Calculated Primary Energy Consumption (TBtu/yr)			
		CT	SOA	PM	TM***	CT	SOA	PM	TM***
Glass Fiber Production									
Batching	737	1,054	818	567	0	0.78	0.60	0.42	0.00
Melting		3,931	2,368	1,462	465	2.90	1.74	1.08	0.34
Fiberization		1,160	957	615	-465	0.85	0.71	0.45	-0.34
Finishing		829	732	374	0	0.61	0.54	0.28	0.00
Overall – Fiber Production			6,974	4,875	3,017	0	5.14	3.59	2.22
Resin Production									
Epoxy resin	737	40,105	32,084	20,021	-115	29.55	23.64	14.75	-0.08
Polyurethane resin		27,355	21,884	13,655	-188	20.15	16.12	10.06	-0.14
Polypropylene (PP)		11,822	9,458	4,631	-1163	8.71	6.97	3.41	-0.86
High density polyethylene (HDPE)		14,617	9,527	4,664	-1744	10.77	7.02	3.44	-1.28
Polyvinyl chloride (PVC)		15,261	11,109	5,439	-969	11.24	8.18	4.01	-0.71
Polystyrene (PS)		18,099	13,887	6,799	-470	13.33	10.23	5.01	-0.35
Composite Product Forming									
Prepreg	1,473	53,238	42,591	40,887	0	39.22	31.38	30.12	0.00
Sheet or bulk molding compound		4,658	3,727	3,578	0	3.43	2.75	2.64	0.00
Open molding (hand lay-up or spray up)		5,805	3,506	3,366	0	4.28	2.58	2.48	0.00
Filament winding		3,594	2,875	2,760	0	2.65	2.12	2.03	0.00
Pultrusion		4,126	3,301	1,505	0	3.04	2.43	1.11	0.00
Injection molding		8,651	2,863	2,474	0	6.37	2.11	1.82	0.00
Compression molding		7,790	6,232	5,983	0	5.74	4.59	4.41	0.00
Resin transfer molding (including vacuum infusion)		2,014	1,611	1,392	0	1.48	1.19	1.03	0.00
Thermoforming		33,935	27,148	13,031	0	25.00	20.00	9.60	0.00
Cold press		15,705	12,564	12,062	0	11.57	9.26	8.89	0.00
Total for Glass Fiber Reinforced Polymer Manufacturing****		1,473	25,553	20,091	12,911	-58	36.17	28.42	18.00

* Glass fiber production data reflect the total production of finished fibers used in automotive, wind energy, pressure vessel, and aerospace applications. Resin production data indicate the estimated production of all resins for GFRP composites in the application areas, assuming 50 wt% glass fibers. Composites production indicates the total production of GFRP composites (all methods) calculated from the above data.

** Energy intensities are reported in terms of Btu per pound of fibers for glass fiber production (all sub-processes), Btu per pound of resin for resin production, and Btu per pound of composite product (fibers and resin) for composite product forming. The total energy intensity for GFRP composites is reported in Btu per pound of composite product. Feedstock energy is excluded in all values. The conversion from on-site energy intensity to primary was made using process-specific energy mix assumptions (see Appendix A3).

*** For TM, primary energy is equal to the on-site energy because electric conversion is assumed to be perfect in the theoretical minimum case.

**** Total is a representative value assuming a fiber fraction of 50 wt% glass fibers (the median value in seven automotive case studies considered; see Appendix A2). The polymer material was assumed to be the product forming method was assumed to be resin transfer molding. The values included in the total are shown in bold in the table. The formula used for the calculation was: Total GFRP Energy = (0.50*[Fiber Production Energy] + 0.50*[Resin Production Energy] + Product Forming Energy). To determine the total for another GFRP composition, the material-specific energy intensity can be calculated by substituting other table values in this formula.

Appendix A2. Fiber Ratios in Structural Lightweighting Applications

To determine a representative fiber-to-resin ratio for lightweight structural applications, seven automotive case studies were compiled from literature sources (see Table A2-1). Each source referenced was an automotive lightweighting study that described the use of a carbon fiber reinforced polymer (CFRP) composite component in a specific lightweighting application (e.g., a vehicle door or chassis). These case studies would fall under the automotive structural application area considered in this bandwidth report. While all of the case studies involved carbon fiber composites (not glass fiber composites), they are referenced in this report to provide continuity with the carbon fiber reinforced composites study in this series. For the sake of comparison, the same fiber fraction was assumed for both fiber-reinforced composite materials (carbon and glass).

Table A2-1. Fiber/Matrix Polymer Ratios: Automotive Case Studies

Case Study	Polymer Type*	Fiber Ratio, by Weight %	Fiber Ratio, by Volume %	Data Source
Automotive door	Epoxy	55 wt%	50 vol%	Rocky Mountain Institute (2013)
Automotive body	Epoxy	55 wt%	50 vol%	Duflou et al. (2009)
Automotive chassis	Epoxy	69 wt%	64 vol%	Suzuki & Takahashi (2005)
Automotive body	PP	46 wt%	32 vol%	Suzuki & Takahashi (2005)
Automotive floor pan	Polyester	31 wt%	34 vol%	Das (2011)
Automotive energy absorber (low)	Epoxy	40 wt%	35 vol%	Jacob et al. (2005)
Automotive energy absorber (high)	Epoxy	50 wt%	45 vol%	Jacob et al. (2005)

* assumed densities were 1.6 g/cm³ for fibers; 1.3 g/cm³ for epoxy resin; 0.9 g/cm³ for polypropylene; and 1.9 g/cm³ for polyester.

The CFRP composites described in these seven case studies ranged in composition from 31% to 69% carbon fiber by weight (32 to 64% by volume). The average value was 49 wt% CF and the median value was 50 wt% CF. Based on these statistics, a 50:50 ratio of fibers to polymer resin (by weight) was assumed to be representative of structural composites for the purposes of this study.

Appendix A3. Energy Mix Assumptions

The fuel and electricity requirements for manufacturing processes depend strongly on the specifics of the process: motor-driven processes such as conveyer belts and mixers typically use mostly electric energy, whereas thermal processes generally use mostly fuel energy. In this study, energy mixes were assumed for each sub-process to maximize the accuracy of conversions between on-site and primary energy intensity and consumption (Table A3-1). These energy mixes were generally drawn from the same sources that were used for baseline energy intensity data. Normally the steam generation and transmission losses would be accounted for when converting from on-site to primary energy consumption, but the sources used in this report did not provide that level of detail for the fuel energy data provided. Consequently, the primary energy intensities may be considered conservative as they only contain off-site electricity generation and transmission losses. Unless otherwise specified in the reference, composite product forming processes were assumed to be 100% electric, which is consistent with several sources (Schepp (2006), Das (2011), Thiriez (2006)).

An electricity generation efficiency of 32.3% was used to calculate off-site electricity generation losses. This value was calculated by dividing the total electricity sales to the industrial sector in 2010 by the sum of electricity sales and electricity generation losses, based on data from the U.S. Energy Information Administration's Monthly Energy Review (EIA (2016)). The formula used to convert between on-site and primary consumption was as follows:

$$E_{primary} = E_{onsite} \left(f_{fuel} + \frac{f_{elec}}{\varepsilon} \right)$$

where $E_{primary}$ and $E_{on-site}$ are the primary and on-site energy consumption values (or energy intensities), respectively, f_{fuel} and f_{elec} are the fractions of fuel and electricity usage for the process, respectively, and ε is the electricity generation efficiency.

Table A3-1. Energy Mix Assumptions for GFRP Composite Manufacturing Processes

Process Subarea or Sub-Process	Fuel %	Electric %	Data Source
Glass Fiber Production			
Batching	0.0%	100.0%	Rue (2007)
Melting			
<i>Melting: Furnace</i>	0.0%	100.0%	Rue (2007)
<i>Melting: Oxygen Production</i>	99.0%	1.0%	Rue (2007)
Fiberization	74.0%	26.0%	Rue (2007)
Finishing	95.0%	5.0%	Rue (2007)
Resin Production: Thermosetting Resins			
Epoxy resin	91.9%	8.1%	PlasticsEurope (2006)
Polyurethane resin	33.2%	66.8%	PlasticsEurope (2005a)
Resin Production: Thermoplastic Resins			
Polypropylene (PP)	39.8%	60.2%	PlasticsEurope (2014a)
High density polyethylene (HDPE)	45.8%	54.2%	PlasticsEurope (2014b)
Polyvinyl chloride (PVC)	68.2%	31.8%	PlasticsEurope (2005b)
Polystyrene (PS)	67.4%	32.6%	PlasticsEurope (2012)
Composite Product Forming: Intermediate (Semi-finished) Manufacturing Methods			
Prepreg	0.0%	100.0%	<i>Best engineering judgment*</i>
Sheet or bulk molding compound	0.0%	100.0%	<i>Best engineering judgment*</i>
Composite Product Forming: Direct Forming Methods			
Open molding (hand lay-up or spray up)	23.9%	76.1%	USLCI (2012)
Filament winding	0.0%	100.0%	<i>Best engineering judgment*</i>
Pultrusion	0.0%	100.0%	<i>Best engineering judgment*</i>
Injection molding	0.0%	100.0%	<i>Best engineering judgment*</i>
Compression molding	6.5%	93.5%	USLCI (2012)
Resin transfer molding (including vacuum infusion)	59.8%	40.2%	USLCI (2012)
Thermoforming	0.0%	100.0%	<i>Best engineering judgment*</i>
Cold press	0.0%	100.0%	<i>Best engineering judgment*</i>

*Unless otherwise specified in the reference, all composite production methods were assumed to be 100% electric, which is consistent with several sources (Schepp (2006), Das (2011), Thiriez (2006)).

Appendix A4. State of the Art and Practical Minimum (R&D) Technologies Considered

The SOA and PM energy intensity for glass fiber composite manufacturing was determined based on the technologies outlined in Table A4-1. The applicability column indicates the subarea/sub-process where the technology is considered for application. The percent savings over the PM baseline is estimated, along with a brief explanation (Note that the SOA baseline is considered equal to the CT energy intensity, and the PM baseline energy intensity is considered equal to the SOA energy intensity in this study). Some technologies in Table A4-1 were considered but not included in the final SOA or PM model. The excluded technologies were considered incompatible with PM technologies already included in the model, or it was determined that the additional energy savings from the technology were negligible.

Table A4-1. Details of Practical Minimum Technologies Considered

Technology Name	Description	Applicability	Explanation of energy savings assumptions	Percent savings (over baseline energy)	Included in SOA calculations?	Included in PM calculations?	Reference
Glass fiber recycling	Use of recycled fiber content in products reduces energy requirements as virgin fibers are generally more energy intensive to produce than recycled fibers.	Fiber Production	An 88% energy savings is assumed for each kg of CFRP replaced by recycled content (Kim (2014)). SOA recycled content is assumed to be 10% (Gardiner (2014)); PM recycled content is assumed to be 40%.	9% [SOA] 24% [PM]	Yes.	Yes.	Gardiner (2014); Kim (2014)
Process control systems	Advanced sensors and control systems enable continuous monitoring and optimization of heat inputs and other parameters for fuel savings. Further, process controls in forehearths, such as gob weight in container glass, tin bath temperature in float glass, and quality controls reduce the number of rejects while increasing productivity and saving energy.	Fiber Production	A 3% savings was assumed for fiber production processes based on increased yields (Worrell (2008)). An additional 3.5% savings was assumed for process controls in forehearths used in fiberization, where additional technology opportunities exist in controlling parameters such as gob weight (Worrell (2008)).	3% [Batching, Melting] 6.5% [Fiberization]	Yes.	Yes.	Worrell (2008)

Motor re-sizing or VSDs	Motors and pumps that are improperly sized cause energy losses that could be avoided with an appropriately sized motor or a variable speed drive motor.	Batching; Finishing	Worrell <i>et al.</i> estimated a typical energy savings of 8-15% from VSDs for conveyer belt systems used in glass batching. The range was averaged to come up with an overall savings of 12% for batching, which was applied only to the electric portion of the energy use	12%	Yes.	Yes.	Worrell (2008); Worrell (2010)
New grinding technologies (such as fine grinding of glass with centrifugal ball mill)	Use of more efficient grinding technology, such as centrifugal ball mills with vertical axis and continuous operation (RM mills)	Batching	Sommariv <i>et al.</i> reported 15% lower specific energy consumption for RM mills, compared to continuous and horizontal axis ball mills. This analysis assumes that grinding technology is used for cullet, assumes cullet use of 50%, and assumes grinding and milling accounts for 80% of cullet batch preparation energy intensity. Therefore, a 15% reduction in grinding and milling energy equates to $15\% \times 40\% \times 80\% =$ a 5% of total batching energy use reduction.	5%	No. This is an R&D opportunity.	Yes.	Sommariv (2015)
Fluxing agents and other additives to batching solution	Optimum glass batching compositions (including the addition of lithium or mixed alkali additives) can reduce energy required to melt the glass.	Melting	Hains <i>et al.</i> reported energy savings of 3-10% from lithia (Li ₂ O) additives and 2-5% from mixed alkali additives. A 4% energy savings was assumed. Note that the benefits of this technology occur in the melting stage, although it is implemented during batching.	4%	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	Hains (2009)

BANDWIDTH STUDY ON ENERGY USE AND POTENTIAL ENERGY SAVING OPPORTUNITIES IN U.S. GLASS FIBER REINFORCED POLYMER MANUFACTURING

Increased cullet rate	Use of cullet and/or filter dust in the glass batch can reduce melting energy.	Melting	It is estimated that a 2.5% reduction in melting energy use results from every 10% increase in cullet. A 10% savings was assumed for the analysis. Note that the benefits of this technology occur in the melting stage, although it is implemented during batching.	10%	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	Worrell (2008)
Reduced batch wetting	A small quantity of water is added to the glass batch to reduce dust and prevent separation and non-homogeneity in the batch during transport, but this water increases energy use because it must be evaporated in the furnace. Reducing water content saves energy.	Melting	Worrell <i>et al.</i> indicated that a 1% reduction in the moisture content can provide fuel savings of 0.5% in the glass melting furnace. A 1% total savings was assumed.	1%	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because the melting SOA value was drawn from literature, not calculated.	Worrell (2008)
Batch and cullet preheating	Waste heat from the furnace is used to preheat the incoming cullet batch, reducing energy losses.	Melting	Worrell <i>et al.</i> estimated energy savings of 12% when installed in an oxy-fuel glass melting furnace.	12%	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	Worrell (2008)
Minimization of excess air in furnace	Non-optimal air/fuel ratios reduce furnace efficiencies. Reduction of excess air in the furnace reduces energy consumption.	Melting	Worrell <i>et al.</i> reported that the glass manufacturer Lax & Shaw (U.K.) demonstrated an energy savings of 12% from improved sealing and insulation.	12%	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	Worrell (2008)

Low-NOx burner	Low-NOx burners can provide increased heat transfer rates and reduced flame temperatures, increasing furnace efficiency.	Melting	Worrell <i>et al.</i> reported that Air Liquide (France) had demonstrated a 5% savings from this technology compared to conventional oxy-fuel burners.	5%	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	No. This is a best practice technology, but was not included because melting SOA value was drawn from literature, not calculated.	Worrell (2008)
More efficient forehearths or oxygen-gas-fired forehearths	Replacement of old forehearths for efficient electric forehearths or oxy-fuel fired forehearths can provide energy savings.	Fiberization	There are several energy savings estimates; some as high as 70% (Worrell (2010), Linde (2016), Praxair 2016). This analysis assumes energy savings of 40% (a more conservative estimate). It also assumes that forehearths account for 30% of all forming energy use for glass fibers. Therefore savings are estimated as $40\% \times 30\% = 12\%$.	12%	No. This is an R&D opportunity.	Yes.	Worrell (2010), Linde (2016), Praxair (2016)
Improved drying and curing of fibers	After quenching molten glass during fiberization, water must be removed in a time-consuming drying process. New gravity and filtration technologies can reduce drying time.	Finishing	Worrell <i>et al.</i> reported that the Viox Corporation was able to reduce drying time from 58 to 72 hours to 11 hours per batch. Based on this reduction, a 30% savings was assumed.	30%	No. This is an R&D opportunity.	Yes.	Worrell (2008); Stalam (2016); Adasan (2016)

Plastics recycling and recovery	Recycling of plastics is currently very limited in composites, but mechanical and other separation technologies could enable reuse.	Resin Production	Martin <i>et al.</i> reported a 70% energy savings with a 70% applicability for thermoplastic (TP) resin production (49% savings). Thermosets are more difficult to recycle, but technologies exist; see e.g. Yang (2012). A 70% savings with an applicability of 50% (35% savings) was assumed for thermoset (TS) resin production.	49% [TP]; 35% [TS]	Yes	Yes.	Martin (2000); Hopewell (2009); Yang (2012)
Barrel insulation	Barrel insulation in closed molding systems enables shorter start-up times and reduces energy use through mitigation of thermal losses.	Injection Molding; Resin Transfer Molding; Vacuum-Assisted Resin Infusion	Schepp <i>et al.</i> estimated that barrel insulation could reduce heating energy by 7% to 25%. A 10% savings was assumed for the applicable composite molding techniques.	10%	No. This is an R&D opportunity.	Yes.	Schepp (2006)
Infrared heating with emissivity matching	Infrared (radiant) heaters can save heating energy when the IR emissivity is well matched to the thermal characteristics of the polymer material	Pultrusion; Thermoforming	Schepp <i>et al.</i> estimated that radiant heaters could reduce energy use by 50%.	50%	No. This is an R&D opportunity.	Yes.	Schepp (2006)
Improved die design	Proper die design (e.g., achieved through simulation) could reduce scrap rates and improve throughput.	Pultrusion	Schepp <i>et al.</i> estimated that rejected product (and the corresponding energy use) could be reduced by 5% through improved die design.	5%	No. This is an R&D opportunity.	Yes.	Schepp (2006)
Process integration/pinch analysis	Process intensification leverages synergies in systems of components working together. Strategies include size and performance matching to reduce bottlenecks (the "pinch")	Cross-Cutting (all subareas and sub-processes)	Martin <i>et al.</i> estimated an energy savings of 10% with 40% applicability, or 4% savings overall.	4%	No. This is an R&D opportunity.	Yes.	Martin (2000)

In cases where more than one technology was considered for a given subarea/sub-process, the following calculation was used:

$$PM = PM_{Baseline} * [(1 - P_1) * (1 - P_2) * ... * (1 - P_n)]$$

where PM is the practical minimum energy intensity, $PMBaseline$ is the baseline energy intensity (i.e., the SOA energy intensity), and P_1, P_2, \dots, P_n are the percent savings for each of the n PM technologies included in the model. Energy savings from different technologies were not considered additive; rather this formula considers technologies as compounding when more than one is applicable to a certain subarea. Energy savings from cross-cutting technologies were applied across all subareas and sub-processes as part of the compounded savings estimate.

Appendix A5. Calculated Energy Intensity of Oxygen Production

Some of the current average, state-of the art, and practical minimum estimates for glass melting used in this study involve the use of oxygen-gas burners, instead of conventional air-gas burners. In cases where the published data sources used in the analysis did not include the energy used to produce oxygen, energy intensity estimates for glass melting where adjusted to include the energy intensity of oxygen generation.

There are three main processes currently used to produce oxygen, namely vacuum swing absorption (VSA), cryogenic air separation, and pressure swing absorption (PSA). The cryogenic oxygen production process has the lowest energy intensity of the three approaches, but is mainly used for large production volumes. Smaller production volumes commonly use the VSA or PSA methods (Rue (2007)). Because of its higher efficiency, adjustments made in this study to the state of the art and practical minimum melting energy intensities assume that oxygen is produced on site using the cryogenic process, without taking into consideration its practicality for small glass production volumes. The adjustment made to the current typical melting energy intensity assumes that oxygen is produced on site using the VSA process. In the case of current typical estimate, the energy intensity of oxygen production has been scaled to 75% to account for facilities that still use recuperative furnaces (an older furnace technology that does not require oxygen production). Rue *et al.* estimates that 75% of current facilities producing textile and reinforcement glass fibers utilize oxygen-gas-fired furnaces (Rue (2007)).

Table A3-1 shows the data used to estimate the on-site energy intensity of oxygen production using each process. The estimated energy required to make oxygen is multiplied by the tons of oxygen used per ton of glass product to estimate the required energy needed to produce oxygen, per ton of glass. This analysis estimates the energy intensity of oxygen generation using the VSA, PSA, and cryogenic processes at 0.6 Btu/ton of glass, 0.8 Btu/ton of glass, and 0.2 Btu/ton of glass, respectively.

Table A3-1. Calculated On-site Energy Intensity of VSA, PSA, and Cryogenic Oxygen Production

Tons of oxygen per ton of glass*		Furnace capacity tons per day*	Electricity Consumption VSA Process (MMBtu/ton of oxygen)**	Electricity Consumption PSA Process (MMBtu/ton of oxygen)**	Electricity Consumption Cryogenic Process (MMBtu/ton of oxygen)***	Calculated Energy Intensity of VSA Oxygen Generation (MMBtu/ton of glass)	Calculated Energy Intensity of PSA Oxygen Generation (MMBtu/ton of glass)	Calculated Energy Intensity of Cryogenic Oxygen Generation (MMBtu/ton of glass)
Min	Max							
0.2	0.3	40-120	2.1	2.6	0.75	0.6	0.8	0.2

* Source: (ACS (1993))

**Source: (Rue (2007))

*** Source: (NETL (2007)). Electricity consumption of 220 kWh/ton of oxygen (at 99% oxygen purity) converted to Btu/ton of oxygen using an energy conversion factor of 3.412 Btu per kWh.

U.S. DEPARTMENT OF
ENERGY

Office of
**ENERGY EFFICIENCY &
RENEWABLE ENERGY**
ADVANCED MANUFACTURING OFFICE

For more information, visit: energy.gov/eere/amo

DOE/EE-1666 • September 2017