

DOE Bioenergy Technologies Office (BETO) 2021 Project Peer Review

Identifying Performance Advantaged Biobased Chemicals Utilizing Bioprivileged Molecules

DOE BETO BEEPS DE-EE0008492

Topic Area 3: Performance Advantaged Bioproducts (PABP)

3/10/21

Performance Advantaged BioProducts

Brent H. Shanks


Iowa State University

This presentation does not contain any proprietary, confidential, or otherwise restricted information

Performance Advantaged Molecules

- Challenges:
 - Biobased chemicals developed primarily through retrosynthesis.
 - Chemical structures available through biology nearly “infinite.”
 - Performance advantaged chemical structure in end use application difficult to predict *a priori*.
 - No systematic strategies.
- Opportunities:
 - Bioprivileged molecules as synthetic platform species.
 - Developments in computational methods (automated reaction network generation, data mining).
 - Literature over the past 100 years contains many examples of molecule screening.
 - Team had interesting set of initial structures for organic corrosion inhibitors and flame retardant polymers (nylon 6,6) and these areas are searching for new molecules.

Project Overview



Project Management

Overall Lead: B. Shanks (ISU)

Task 2: Identification of Novel Enhanced Organic Corrosion Inhibitors

- G. Kraus, B. Shanks (ISU)

Task 3: Identification of Novel Enhanced Flame Retardant Nylons

- J.P. Tessonnier, E. Cochran, B. Shanks (ISU)

Task 4: Construction and Application of Recurrent Neural Network Model

- J. Pfaendtner, D. Beck (UW)

Task 5: Construction and Application of Reaction Network Generation Framework

- L. Broadbelt (NU)

Technology Risks/Mitigation

- Screening protocol for novel molecules
 - Developing representative test
 - Sample size
- Computational strategy
 - Data mining has precedent
 - Reaction network generation builds from existing platform
 - Integration is unique
- Technology translation
 - Industrial connection

Approach

Phase 1: Project Component Development


- Initial synthetic “libraries” for each application
- Development of recurrent neural network (RNN) and reaction network generation (RNG) framework
- Second iteration of synthetic libraries for each application

Phase 2: Integration of Project Components


- Passing structures from RRN to RNG for candidate molecule identification
- Synthesize libraries from candidate molecules

| | Key Milestones & Deliverables |
|---------------|--|
| Year 1 | <ul style="list-style-type: none">• Identification of at least two novel corrosion inhibitors• Nylon modified with 3-hexenedioic acid screened |
| Year 2 | <ul style="list-style-type: none">• Initial set of at least 5 novel molecules identified• First set of data mined candidate molecules found |
| Year 3 | <ul style="list-style-type: none">• Data mined candidate molecules synthesized and tested - ≥ 5 novel molecules identified• Integrated computational process developed for finding novel chemicals. |


Initial Corrosion Inhibitor Set



Urotropin synthesis




Opuntiol speculated as promising performance (*Opuntia elatior*)*



CBiRC triacetic acid lactone

Electrochemical impedance spectroscopy screening




$$\text{IE}\% = \left(\frac{R_p - R_{p0}}{R_p} \right) \times 100$$

where R_p and R_{p0} are the values of the polarisation resistance with and without inhibitor, respectively.

*Loganayagi et al., *ACS Sustainable Chemistry & Engineering* (2014), **2**, 606-613.

Initial Polymer Set



Conventional nylon 6,6: adipic acid + hexamethylenediamine

Flame retardant nylon 6,6: (adipic acid/3-hexenedioic acid) + hexamethylenediamine


} Same polymerization procedure
Similar thermal and mechanical properties

UPA-x polymers formed from blends of **x** mol % AA and HAD (10 samples)

TGA Screening for Char Formation




Recurrent Neural Network Framework




- Concept: the “data mining + similarity” workflow will produce candidate molecules for the reaction network generator
 - Hypothesis: “target” molecules will have ideal properties for applications, can be readily synthetically upgraded from “candidates” due to chemical similarity

Reaction Network Generation Framework



Integration of Computational Tasks



Specific Product Impact: Performance and environmental impact



- Organic corrosion inhibitors to replace inorganics
- Flame retardant polymers without co-extruded molecules

Broader Impact:





















- Value-added products that can help enable biorefineries
- Systematic strategy to identify and develop performance advantaged biobased chemicals

Corrosion Inhibitor Libraries

1st and 2nd Generation Libraries




Corrosion Inhibitor Libraries – H₂SO₄

| | | | | | | | | |
|---------|------------------|---|--|---|---|---|---|---|
| Label | 4HC |  |  |  |  |  |  |  |
| Rct/Ohm | 13 | 430 | 397 | 478 | 269 | 398 | 133 | 11 |
| IE | -23% | 96% | 96% | 97% | 94% | 96% | 88% | -45% |
| Label | TAL |  |  |  |  |  |  |  |
| Rct/Ohm | 16 | 77 | 73 | 126 | 44 | 306 | 415 | 229 |
| IE | 0% | 79% | 78% | 87% | 64% | 95% | 96% | 93% |
| Label | Urotropin |  |  |  |  |  |  | |
| Rct/Ohm | 23 | 18 | 19 | 99 | 71 | 145 | 270 | |
| IE | 30% | 11% | 16% | 84% | 77% | 89% | 94% | |

Polymer: 3HDA Content Evaluated

- UPA-x polymers with blends of x mol % HDA replacement of AA




| Sample | Anaerobic Char (%) | Aerobic Char (%) |
|------------|--------------------|------------------|
| Commercial | 4.4 ± 0.8 | 25.1 ± 0.9 |
| UPA-0 | 3.7 ± 1.3 | 26 ± 2 |
| UPA-5 | 6.7, 6.7 | 30.6, 26.3 |
| UPA-10 | 7.0, 8.3 | 29.9, 30.3 |
| UPA-20 | 10.0, 8.9 | 28.6, 28.9 |
| UPA-30 | 9.7, 10.5 | 30.2, 27.9 |

| Sample | T _m (°C) | ΔH _m (J/g) | T _c (°C) | ΔH _c (J/g) | M _n (kDa) | M _w (kDa) | PDI |
|--------|---------------------|-----------------------|---------------------|-----------------------|----------------------|----------------------|------|
| UPA-0 | 257.1 | 49.6 | 223.9 | 43.6 | 17.1 | 34.3 | 2.01 |
| UPA-5 | 253.6 | 38.6 | 219.3 | 42.2 | 16.7 | 34.0 | 2.04 |
| UPA-10 | 247.0 | 35.8 | 211.3 | 38.7 | 16.3 | 33.2 | 2.04 |
| UPA-20 | 233.4 | 25.6 | 192.1 | 32.1 | 16.2 | 33.0 | 2.03 |

Annealed ISO 527-2 1BB bars, 7-10 replicates: Similar **toughness, tensile modulus, max stress, mass strain**

Workflow for Generic Candidate Molecules



Reaction Network Candidate Pruning


Starting Candidates

| Formula | Compounds |
|-------------|-----------|
| $C_4H_xO_y$ | 5,706 |
| $C_5H_xO_y$ | 13,271 |
| $C_6H_xO_y$ | 35,542 |
| $C_7H_xO_y$ | 57,043 |

Final Pruning

| Step | C5 | C6 |
|------------------------|------------|------------|
| Product Count | 277 | 390 |
| Product Rank | - | 14 |
| Thermodynamics | 91 | 41 |
| Known Products | 4 | 34 |
| Literature of Products | 4 | 57 |
| % Unknown | 51 | 314 |
| Patents/Literature | 113 | 45 |
| Toxicity | 12 | 35 |
| CANDIDATES | 104 | 103 |

RNN for Corrosion Inhibitors



```
{'name': ['imidazoline', '2-imidazoline'],
'role': 'product',
'inhibition_efficiency': {'value': '99.3', 'units': '%'},
'LUMO': {'value': '6.048 - 6.720', 'units': 'eV'},
...
'SMILES': 'N\1=C\NCC/1',
'sentiment_phrase': 'good corrosion inhibitor'}
```

Articles: **~100,000**
Extracted molecules: **~22,000**
Initial candidates: **60***

* High similarity scores

Future Work – Corrosion Inhibitors

- Additional characterizations with best candidates
 - Electron microscopy
 - Quantum chemical calculations
 - Molecular dynamic simulations
 - Adsorption isotherm studies
- Chemical structures suggested by computational work
- Technology translation
 - Connect with corrosion inhibitor companies
 - Understand commercial requirements for further development of identified organic corrosion inhibitors

Future Work – Flame Retardant Nylon

- Additional testing with best polymer candidates
 - Polymer physical properties (thermal - <20 mg, mechanical - ~10 g)
 - Microcalorimetry screening
 - Flammability testing
- Initial tethered chemical structures
- Tethered chemical structures suggested by computational work
- Technology translation
 - Connect with polymer companies
 - Establish plan for further development of identified flame retardant nylons

Summary

- 13 high performing organic corrosion inhibitors identified
- Improved charring “nylon 6,6” synthesized with good physical properties
- RNN and RNG computational frameworks established
- First set of prospective corrosion inhibitors handed off from RNN to RNG
- Key future work
 - Proposed bioprivileged molecules for corrosion inhibitor library generation
 - Second test of computational framework for tethered moieties to create flame retardant nylon polymers

Quad Chart Overview

Timeline

- 10/1/18
- 12/31/21

| | FY20 Costed | Total Award |
|---------------------------|-------------|-------------|
| DOE Funding | \$923,061 | \$2,500,000 |
| Project Cost Share | \$326,676 | \$625,000 |

Project Partners

- Northwestern University
- University of Washington

Project Goal

Advance two technological areas; a) novel molecules with improved performance in the end use application of organic corrosion inhibitors and flame retardant nylon polymers and b) development of a systematic process for identifying biomass-derived molecules with improved performance in end use applications. Use the two application areas for aiding the construction of a broader systematic process for novel molecule identification.

End of Project Milestones

- Data mined candidate molecules synthesized and tested - ≥ 5 novel molecules identified with $>10\%$ performance improvement
- Integrated computational process developed for finding novel chemicals.

Funding Mechanism

FOA-0001916 Bioenergy Engineering for Products Synthesis (BEEPS) - 2018
Topic Area 3: Performance Advantaged Bioproducts (PABP)

Thank You

Responses to Previous Reviewers' Comments

- If your project has been peer reviewed previously, address 1-3 significant questions/criticisms from the previous reviewers' comments which you have since addressed
- Also provide highlights from any Go/No-Go Reviews

Note: This slide is for the use of the Peer Reviewers only – it is not to be presented as part of your oral presentation. These Additional Slides will be included in the copy of your presentation that will be made available to the Reviewers.

Publications, Patents, Presentations, Awards, and Commercialization



- Carraher, J.M., Carter, P., Rao, R.G., Forrester, M.J., Pfennig, T., Shanks, B.H., Cochran, E.W., and Tessonier, J.-P., "Solvent-driven isomerization of cis,cis-muconic acid for the production of specialty and performance-advantaged cyclic biobased monomers," *Green Chemistry*, **22**, 6444-6454 (2020)
- Dollar, O., Joshi, N., Beck, D.A.C., and Pfaendtner, J. "Giving Attention to Generative VAE Models for *de novo* Molecular Design," *Nature Communications*, submitted (2020)
- Lopez, L.M., Shanks, B.H., and Broadbelt, L.J., "Identification of Bioprivileged Molecules: Expansion of a Computational Approach to Broader Molecular Space," *Molecular Systems Design & Engineering*, submitted (2021)
- Abdolmohammadi, S., Forrester, M.J., Lin, F.-Y., Gansebom, D., Nelson, J.W., Matthiesen, J.E., Hernández, N., Shanks, B.H., Tessonier, J.-P., and Cochran, E.W., "Analysis of the Amorphous and Interphase Influence of Comonomer Loading on Polymer Properties Towards Forwarding Bioadvantaged Copolyamides," *Green Chemistry*, submitted (2021).
- Tessonier, J.P., Shanks, B.H., Cochran, E.W., Hadel, J.E., Dell'Anna, M.N. and Carter, P., "Isomerization of Cyclohexenedicarboxylic Acid and its Derivatives," United States Patent application, 2020.
- Shanks, B.H., Kraus, G.A., Bradley, W., Huo, J. and Podolak, K., "Heteroaryl-Thio-Substituted Pyrones," United States Patent application, 2020.
- "Developing Performance-Advantaged Chemicals Utilizing Bioprivileged Molecules: Organic Corrosion Inhibitors" with Huo, J., Bradley, W., Podolak, K., Ryan, B., Roling, L.K., Kraus, G.A., Annual Meeting, American Institute of Chemical Engineers, virtual, November, 2020.

Note: This slide is for the use of the Peer Reviewers only – it is not to be presented as part of your oral presentation. These Additional Slides will be included in the copy of your presentation that will be made available to the Reviewers.

